

CAR CARE Water Repelling Agent HP 14

Properties: Low viscous water repelling agent for glass surfaces, e. g. windows, mirrors, shower cabin walls and solar systems or plastic surfaces, e. g. visors of helmets. HP 14 forms an extremely smooth layer on the treated surface. Thus, water rinses off very rapidly.

Apply HP 14 with a cloth, wait for 5 min, and then rub-out.

| Ingredient | Weight [%] | Description |
|---------------------------|------------|--------------------------------|
| 1 WACKER® PDM-Siloxane | 9.8 | Silicone fluid |
| 2 WACKER® 1035 | 0.2 | Silicone resin solution |
| 3 Isopropyl alcohol | 80.0 | |
| 4 Mineral spirit 100/140° | 9.0 | Hydrocarbons free of aromatics |
| 5 Sulfuric acid conc. | 1.0 | |

Procedure: Mix the ingredients in the order given at room temperature.

| | | | |
|-------------------|---------|------------------------|--|
| Suppliers: | 1, 2 | Wacker Chemie AG | www.wacker.com |
| | 3, 4, 5 | VWR International GmbH | www.vwr.com |

Further Information:

Product data sheets and material safety data sheets of WACKER® - products can be ordered from our WACKER-subsiidiaries or via the Internet www.wacker.com.

For further questions, please contact our WACKER® SILICONES INFO-SERVICE:

Wacker Chemie AG
WACKER SILICONES
Hanns-Seidel-Platz 4
D-81737 München

e-mail: info.silicones@wacker.com
phone: +49 89 6279-0

WACKER® is a registered trademark of Wacker Chemie AG.

The data presented in this starting formulation are in accordance with the present state of our knowledge. The information given in this starting formulation should be checked by preliminary trials because of conditions during processing over which we have no control, especially where other companies' raw materials are also being used. The information provided by us do not absolve the user from the obligation of investigating the possibility of infringement of third parties' rights and, if necessary, clarifying the position. Recommendations for use do not constitute a warranty, either expressed or implied, of the fitness or suitability of the product for a particular purpose.