

**WACKER**

CREATING TOMORROW'S SOLUTIONS

VINNOL®

VINNAPAS®

EUROPEAN PRODUCT PORTFOLIO

VINNAPAS® AND VINNOL® –  
DISPERSIONS FOR NONWOVENS  
AND TECHNICAL TEXTILES

# PRODUCT OVERVIEW

Grade	Polymer base <sup>1</sup>	Typical General Characteristics							Stabilization System	
		Solids content (ISO 3251) (residue after drying) [%]	Viscosity brookfield RVT at 23°C 20rpm (ISO 2555) [mPa.s]	pH (ISO 976)	Minimum film-forming temperature (approx.) (ISO 2115) [°C]	Glass transition temperature Tg (DSC) (approx.) [°C]	Predominant particle size (approx.) [µm]	Film	Protective colloid/emulsifier system	Grade
<b>VINNAPAS® homopolymer dispersions</b>										
VINNAPAS® DPN 36T	VAc	52 ± 1	25,000 ± 7,000	4 – 6	2	28	1	brittle	PVOH <sup>2</sup>	VINNAPAS® DPN 36T
VINNAPAS® DP 500	VAc	50 ± 2	35,000 ± 5,000	4.5 – 5.5	14	33	1 – 3	brittle	PVOH <sup>2</sup>	VINNAPAS® DP 500
VINNAPAS® DP 55	VAc	55 ± 2	3,000 ± 1,500	4 – 5	14	33	1 – 3	brittle	PVOH <sup>2</sup>	VINNAPAS® DP 55
VINNAPAS® DP 600	VAc	60 ± 2	35,000 ± 6,000	4 – 5.5	14	33	1 – 3	brittle	PVOH <sup>2</sup>	VINNAPAS® DP 600
VINNAPAS® M 50/300	VAc	50 ± 1	1,000 ± 300	4 – 5	14	35	0.5 – 2	brittle	PVOH <sup>2</sup>	VINNAPAS® M 50/300
<b>VINNAPAS® vinyl acetate-ethylene copolymer dispersions</b>										
VINNAPAS® EP 177	VAc-E	60 ± 1	3,800 ± 1,000	4 – 5	0	3	0.9	soft	PVOH <sup>2</sup>	VINNAPAS® EP 177
VINNAPAS® EP 740	VAc-E	55 ± 1	2,400 ± 400	4 – 5	0	5	0.8	soft	PVOH <sup>2</sup>	VINNAPAS® EP 740
VINNAPAS® EF 1577	VAc-E	56 ± 1	1,000 ± 850	3.5 – 5.5	0	10	0.2	tough	Surfactant	VINNAPAS® EF 1577
<b>VINNAPAS® self-crosslinking vinyl acetate copolymer dispersions</b>										
VINNAPAS® 192	VAc-E	52 ± 1	225 ± 175	4.5 – 6	0	10	0.1 – 3	tough	Surfactant	VINNAPAS® 192
VINNAPAS® AN 214	VAc-A	50 ± 1	250 ± 150	4.5 – 5.5	13	30	0.2 – 3	tough	Surfactant	VINNAPAS® AN 214
VINNAPAS® EN 1020	VAc-E	50 ± 1	350 ± 300	3 – 4	0	-8	0.3	soft	Surfactant	VINNAPAS® EN 1020
VINNAPAS® EN 1024	VAc-E	53 ± 1	350 ± 250	4 – 5	0	-11	0.3	soft	Surfactant	VINNAPAS® EN 1024
VINNAPAS® EN 1028	VAc-E	50 ± 1	350 ± 300	4.5 – 5.5	0	-5	0.3	soft	Surfactant	VINNAPAS® EN 1028
VINNAPAS® EN 1033	VAc-E	53 ± 1	300 ± 200	3.5 – 4.5	0	-5	0.3	soft	Surfactant	VINNAPAS® EN 1033
VINNAPAS® EN 428	VAc-E	52 ± 1	200 ± 150	4 – 6	0	-15	0.2 – 0.3	soft	Surfactant	VINNAPAS® EN 428
<b>VINNAPAS® acrylic copolymer dispersions</b>										
VINNAPAS® SAF 364	S/A	50 ± 1	9,000 ± 3,000	7.5 – 8.5	12	20	0.1	tough	Surfactant	VINNAPAS® SAF 364
<b>VINNOL® vinyl chloride co- &amp; terpolymer dispersions</b>										
VINNOL® CE 35	VC-VAc-E	50 ± 1	50 ± 30	6.0 – 7.5	45	40	0.15	brittle	Surfactant	VINNOL® CE 35
VINNOL® CEN 2752	VC-E	50 ± 1	200 ± 150	5.0 – 7.5	5	10	0.2	tough	Surfactant	VINNOL® CEN 2752

Grade	Product Properties							Application Methods				
	Soft hand	Hard hand	Hydrophilic	Hydrophobic	Washproof and solvent resistance	Flame retardant	Heat-sealable/HF-weldabl	Impregnation	Print bonding	Spraying	Foaming	Grade
<b>VINNAPAS® homopolymer dispersions</b>												
VINNAPAS® DPN 36T		●●●	●●		●●			●●				VINNAPAS® DPN 36T
VINNAPAS® DP 500		●●●	●●					●●				VINNAPAS® DP 500
VINNAPAS® DP 55		●●●	●●			●	●●	●●		●		VINNAPAS® DP 55
VINNAPAS® DP 600		●●●	●●				●	●●				VINNAPAS® DP 600
VINNAPAS® M 50/300		●●●	●●			●	●●●	●●		●		VINNAPAS® M 50/300
<b>VINNAPAS® vinyl acetate-ethylene copolymer dispersions</b>												
VINNAPAS® EP 177	●		●			●	●●	●●				VINNAPAS® EP 177
VINNAPAS® EP 740	●		●●			●	●●	●●				VINNAPAS® EP 740
VINNAPAS® EF 1577	●		●●				●	●●		●●●	●●	VINNAPAS® EF 1577
<b>VINNAPAS® self-crosslinking vinyl acetate copolymer dispersions</b>												
VINNAPAS® 192	●		●●●		●●			●●	●●	●●●	●●	VINNAPAS® 192
VINNAPAS® AN 214		●●●	●●●		●●	●		●●	●●	●●●	●●	VINNAPAS® AN 214
VINNAPAS® EN 1020	●●●		●●●		●●			●●	●●	●●●	●●	VINNAPAS® EN 1020
VINNAPAS® EN 1024	●●●		●●		●●			●●	●●	●●●	●●●	VINNAPAS® EN 1024
VINNAPAS® EN 1028	●●●			●●●	●●			●●●	●●	●●●	●●	VINNAPAS® EN 1028
VINNAPAS® EN 1033	●●●			●	●●			●●	●●	●●●	●●	VINNAPAS® EN 1033
VINNAPAS® EN 428	●●●			●●●	●			●●●	●●	●●●	●●	VINNAPAS® EN 428
<b>VINNAPAS® acrylic copolymer dispersions</b>												
VINNAPAS® SAF 364		●●	●●					●●●				VINNAPAS® SAF 364
<b>VINNOL® vinyl chloride co- &amp; terpolymer dispersions</b>												
VINNOL® CE 35		●●●	●			●●●	●●●	●●		●●	●●●	VINNOL® CE 35
VINNOL® CEN 2752			●		●	●●●	●	●●	●●		●●	VINNOL® CEN 2752

These figures are only intended as a guide and should not be used in preparing specifications.

<sup>1</sup> VAc = vinyl acetate

A = acrylic ester

E = ethylene

VC = vinyl chloride

S = styrene

<sup>2</sup> PVOH = poly(vinyl alcohol)

VINNAPAS® and VINNOL® are registered trademarks of Wacker Chemie AG.



**WACKER**

**Wacker Chemie AG**  
Hanns-Seidel-Platz 4  
81737 München, Germany  
Tel. +49 89 6279-1741  
info.nonwoven@wacker.com

[www.wacker.com](http://www.wacker.com)

[www.wacker.com/socialmedia](http://www.wacker.com/socialmedia)



The data presented in this medium are in accordance with the present state of our knowledge but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this medium should be checked by preliminary trials because of conditions during processing over which we have no control, especially where other companies' raw materials are also being used. The information provided by us does not absolve the user from the obligation of investigating the possibility of infringement of third parties' rights and, if necessary, clarifying the position. Recommendations for use do not constitute a warranty, either express or implied, of the fitness or suitability of the product for a particular purpose.