

# ELASTOSIL<sup>®</sup> E60 N RED



## Moisture Curing Silicone Rubber (RTV-1)

ELASTOSIL<sup>®</sup> E60 N RED is a flowable one-part silicone rubber for potting and coating applications. When exposed to air moisture it cures at room temperature to yield a permanently flexible silicone rubber with excellent heat resistance.

Fully vulcanized ELASTOSIL<sup>®</sup> E60 N RED shows long-term stability against weathering, moisture and UV radiation. The silicone elastomer may continuously be exposed to constantly changing climatic conditions, UV radiation and temperature as high as 230 °C (446 °F) without damage.

## Properties

Uncured:

- Flowable, self-levelling
- Fast skin formation at room temperature
- By-product of curing: acetic acid

Cured:

- Medium hardness
- Designed for coating and potting applications
- Recommended service temperature range: -50 °C to +230 °C
- No inhibition of Pt curing silicones
- Suitable for applications with food contact

**Please note:** fully cured ELASTOSIL<sup>®</sup> E60 N RED is suitable for uses under the Recommendation "XV. Silicones" of the BfR and 21 CFR § 175.300 "Resinous and polymeric coatings" and FDA 21 CFR §177.2600 "Rubber articles intended for repeated use", provided that any given limitations on extractable and volatile substances are observed. Residual solvents have to be completely removed from the food contact article.

## Specific features

- Condensation-curing
- Electrically insulating
- Food grade
- General purpose
- Low viscosity
- One-component
- Primerless adhesion to most substrates
- Ready to use
- Resistant to moisture
- UV & weathering-resistant

## Technical data

### Properties Uncured

Property	Condition	Value	Method
Colour	-	red	-
Curing speed	23 °C   50 % r.h	1.9 mm/d	-
Density	23 °C   1013 hPa	1.12 g/cm <sup>3</sup>	ISO 2811 (pycnometer)
Skin formation time	23 °C   50 % r.h	10 - 15 min	-
Viscosity, dynamic	25 °C   0.5 1/S	90000 mPa·s	DIN EN ISO 3219
Viscosity, dynamic	25 °C   25 1/S	65000 mPa·s	DIN EN ISO 3219

These figures are only intended as a guide and should not be used in preparing specifications.

## Properties Cured

Curing Conditions: 14 days at 23 °C and 50 % rel. humidity, 2 mm sheet, no post-curing.

Property	Condition	Value	Method
Color	-	red	-
Density (in water)	23 °C	1.13 g/cm <sup>3</sup>	DIN EN ISO 1183-1 A
Hardness Shore A	-	35	DIN ISO 48-4
Tensile strength	-	2.6 N/mm <sup>2</sup>	ISO 37 type 1
Elongation at break	-	300 %	ISO 37 type 1
Tear strength	-	8.0 N/mm	ASTM D 624 B

These figures are only intended as a guide and should not be used in preparing specifications.

All the information provided is in accordance with the present state of our knowledge. Nonetheless, we disclaim any warranty or liability whatsoever and reserve the right, at any time, to effect technical alterations. The information provided, as well as the product's fitness for an intended application, should be checked by the buyer in preliminary trials. Contractual terms and conditions always take precedence. This disclaimer of warranty and liability also applies particularly in foreign countries with respect to third parties' rights.

## Applications

- Baking Tray Coatings
- Machine Building

## Application details

- Multipurpose grade for coating and potting, in particular for food related applications
- Typical fields of application: household appliances, mechanical engineering, bakeware equipment.

## Processing

### Processing

ELASTOSIL® E60 N RED is a ready-to-use, one-part silicone rubber which starts curing when exposed to air moisture. Typical curing characteristics are given in the table "Properties Uncured".

As RTV-1 silicones require humidity for curing, free access of air moisture to the silicone rubber is essential. Additionally, the vulcanization time of ELASTOSIL® E60 N RED can be greatly reduced by increasing the level of air's relative humidity. Please note that, unlike the initial skin formation, the total curing rate of RTV-1 silicones is limited by moisture's diffusion speed in silicone rubber.

ELASTOSIL® E60 N RED typically is vulcanized at room temperature. Heat curing is recommended only for applications where the silicone rubber is applied as a thin coating (thickness less than 0.5 mm), because otherwise blistering is likely to occur due to the quick release of acetic acid.

After completion of the vulcanization the silicone elastomer may continuously be exposed to constantly changing climatic conditions, UV radiation and high temperature without damage. Cured ELASTOSIL® E60 N RED usually shows good primerless adhesion to many substrates, e.g. glass, ceramics, metals, plastics and powder coatings.

Detailed information about the processing of RTV-1 silicones is given in our brochure "ROOM TEMPERATURE VULCANIZING (RTV) SILICONES - MATERIAL AND PROCESSING GUIDELINES". We recommend running preliminary tests to optimize conditions for the particular application.

#### Removal:

If removal of the silicone from machines, metering and application equipment is necessary, white spirit or similar nonpolar solvents are recommended. However, cleaning ideally should take place before the silicone rubber is fully vulcanized. Cured silicone needs to be rubbed off or removed mechanically, if necessary in combination with a swelling agent (solvent) or a chemical silicone remover.

## Example of Use

### Baking Tray Coatings

ELASTOSIL® E60 N RED is designed to create long-lasting, non-stick coatings for an optimum release of bakery products. Baking trays coated with silicone rubber are particularly suitable for croissants, buns, white bread, brown bread and sourdough bread.

#### Surface Preparation:

Though ELASTOSIL® E60 N RED shows primerless adhesion to many substrates, the trays to be coated should be cleaned prior use in order to remove any dirt, rust, oil or grease. If required, the surface of the trays can be roughened by sandblasting to improve the adhesion of the silicone rubber coating.

#### Priming:

For an optimum of adhesion it is recommended to additionally prime the trays with WACKER® Primer G 790 or WACKER® Primer G 790 TOLUENE FREE. Both primers are best applied by spraying; dipping or brushing is also suitable.

Please note: as a too thick primer layer can reduce adhesion, both WACKER® Primer G 790 and WACKER® Primer G 790 TOLUENE FREE should be applied as a very thin coating only (< 2 µm thickness). In order to minimize the layer thickness, it is recommended to dilute the primers directly before use with a nonpolar and technically dry solvent (cyclohexane, white spirit or a similar aliphatic solvent) in a 1:1 or 1:2 ratio (primer:solvent). Please mind the food compliance of the solvent used for diluting ! For further details regarding priming with WACKER® Primer G 790 or WACKER® Primer G 790 TOLUENE FREE, please revert to the respective technical data sheet.

When the primer solution has been applied, the primed parts must be air dried for at least 15 minutes to allow all solvents to evaporate. Finally, the primer layer is baked at 150 to 170 °C for 20 minutes.

#### Preparation of the coating suspension:

Though ELASTOSIL® E60 N RED is flowable and self-levelling, the product needs to be diluted before use in order to get optimum coating results. Suitable diluents are non-polar, aliphatic solvents such as technically dry cyclohexane, white spirit or a similar aliphatic grade (please mind the food compliance of the solvent used !). A mixing ratio of 1:1 to 2:1 (solvent:silicone rubber) is recommended.

Important: once prepared, the coating mixture has to be stirred continuously in order to prevent the separation of fillers. Furthermore the container should be humidity-tight and must be kept properly closed, because the coating suspension is sensitive to moisture.

#### Coating:

The coating mixture can be applied by any coating method, such as spraying, dipping and brushing. However, airless spraying equipment is particularly recommended, as this avoids premature curing of the silicone rubber suspension during spraying.

Since the film thickness is essential for the durability of the anti-stick coating, the silicone rubber suspension should be applied in a quantity of some 150 g per m<sup>2</sup> (including overspray). Multilayered application is possible, e.g. for baking pans with a complex design. In total, the rubber coating should have a thickness of 150 µm (minimum) to 350 µm (maximum) after curing.

#### Curing:

The curing process already starts during application, in the moment when the coating suspension gets in contact with air moisture. For physical drying it is recommended to store the coated trays for at least 60 minutes at room temperature in order to allow the solvents to evaporate. Subsequently the coating is baked at 250 °C for 1 hour (alternatively: 4 hours at 200 °C).

#### Coating removal (deglazing, restoration):

Coated baking trays and pans can be restored either by pyrolysis at a temperature above 600 °C, followed by cleaning via sandblasting, or by chemical methods (immersion into a highly basic etching bath, followed by thoroughly rewashing the trays with water). Alternatively, the silicone rubber coating can be removed by CO<sub>2</sub> blasting or sandblasting.

## Packaging and storage

### Storage

Store in a dry and cool place.

The 'Best use before end' date of each batch is shown on the product label.

Storage beyond the date specified on the label does not necessarily mean that the product is no longer usable. In this case however, the properties required for the intended use must be checked for quality assurance reasons.

### Safety notes

While curing ELASTOSIL® E60 N RED releases a total of approx. 3.5 % by weight of acetic acid. These vapours should not be inhaled for long periods or in high concentration. Work areas should therefore be well ventilated.

Contact of the uncured silicone rubber with eyes and mucous membranes must be avoided as this can cause irritation. If, despite all protective measures, uncured silicone rubber comes into contact with the skin or eyes, irrigate the affected area immediately with copious amounts of water for several minutes. If the irritation continues, immediately seek medical advice.

Comprehensive instructions are given in the corresponding Material Safety Data Sheets. They are available on request from WACKER subsidiaries or may be printed via WACKER web site <http://www.wacker.com>.

### QR Code ELASTOSIL® E60 N RED



### For technical, quality or product safety questions, please contact:

**Wacker Chemie AG**, Hanns-Seidel-Platz 4, 81737 Munich, Germany  
[info@wacker.com](mailto:info@wacker.com), [www.wacker.com](http://www.wacker.com)

The data presented in this medium are in accordance with the present state of our knowledge but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this medium should be checked by preliminary trials because of conditions during processing over which we have no control, especially where other companies' raw materials are also being used. The information provided by us does not absolve the user from the obligation of investigating the possibility of infringement of third parties' rights and, if necessary, clarifying the position. Recommendations for use do not constitute a warranty, either express or implied, of the fitness or suitability of the product for a particular purpose.