

ELASTOSIL[®] SC 870 A/B



Room Temperature Curing Silicone Rubber (RTV-2)

ELASTOSIL[®] SC 870 A/B is a thixotropic, addition-curing, two-part silicone rubber, forming a mainly closed cell foam. ELASTOSIL[®] SC 870 A/B is perfectly suited for processing with automatic dispensing equipment. It is suitable for CIPG foam gaskets even in 3D geometries due to its outstanding rheology.

Properties

- good processability on automated dispensing equipment
- easy control of mixing quality due to different colors of the components
- no ozone damaging blowing agents
- no release of toxic or strong smelling substances during foaming or curing
- low heat of reaction (max. 40 °C)
- low toxicity of thermal decomposition products
- long-term flexible over a temperature range of -50 °C to +180 °C
- good chemical resistance
- fast foaming and cure
- medium foam density

Specific features

- Compressible
- Foam
- Heat resistant
- Thixotropic
- Two-component

Technical data

Properties Uncured

Property	Condition	A	B	Method
Color	-	black	colorless	-
Density	23 °C	1.05 g/cm ³	1.05 g/cm ³	DIN EN ISO 2811-1
Viscosity, dynamic ⁽¹⁾	23 °C	40000 mPa·s	50000 mPa·s	Brookfield

¹Spindle 5, 2.5UPM

These figures are only intended as a guide and should not be used in preparing specifications.

Properties Catalyzed A+B

Property	Condition	Value	Method
Mix ratio ⁽¹⁾	-	1 : 1	A : B
Pot Life ⁽²⁾	25 °C	150 s	-
Tack-free time	-	10 - 15 min	-

¹(pbw)

²Viscosity dynamic, ISO 3219, D = 1 1/s, time to 200 Pas

These figures are only intended as a guide and should not be used in preparing specifications.

Properties Cured

Curing conditions: 15 min / 50°C, conditioning min. 24 h at 23 °C / 50 % r.h

Property	Condition	Value	Method
Color	-	gray	-
Density	23 °C	0.35 - 0.4 g/cm ³	DIN EN ISO 1183-1 A
Hardness Shore A ⁽¹⁾	-	8 - 12	DIN ISO 48-4
Hardness Shore 00 (with skin)	-	40 - 60	ASTM D 2240
Tensile strength	-	350 kPa	ISO 1798
Elongation at break	-	100 %	ISO 1798

¹(with skin)

These figures are only intended as a guide and should not be used in preparing specifications.

All the information provided is in accordance with the present state of our knowledge. Nonetheless, we disclaim any warranty or liability whatsoever and reserve the right, at any time, to effect technical alterations. The information provided, as well as the product's fitness for an intended application, should be checked by the buyer in preliminary trials. Contractual terms and conditions always take precedence. This disclaimer of warranty and liability also applies particularly in foreign countries with respect to third parties' rights.

Applications

- Appliances Industry
- Automotive Electronics
- Automotive, Aerospace & Railway
- Cured-In-Place-Gaskets (Dry Type)
- Industrial Assembly
- Transportation

Application details

- general purpose foam for gaskets (dispensed foam gaskets)
- especially suitable for 3-dimensional gasket bead
- general purpose high and low temperature resistant sealing material
- suitable for NVH insulation

Packaging and storage

Storage

The 'Best use before end' date of each batch is shown on the product label.

Storage beyond the date specified on the label does not necessarily mean that the product is no longer usable. In this case however, the properties required for the intended use must be checked for quality assurance reasons.

Safety notes

According to the latest findings, the addition-curing silicone rubber ELASTOSIL® SC 870 A/B contains neither toxic or corrosive substances which would require special handling precautions.

Comprehensive instructions are given in the corresponding Material Safety Data Sheets. They are available on request from WACKER subsidiaries or may be printed via WACKER web site <http://www.wacker.com>.

QR Code ELASTOSIL® SC 870 A/B



For technical, quality or product safety questions, please contact:

Wacker Chemie AG, Hanns-Seidel-Platz 4, 81737 Munich, Germany
productinformation@wacker.com, www.wacker.com

The data presented in this medium are in accordance with the present state of our knowledge but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this medium should be checked by preliminary trials because of conditions during processing over which we have no control, especially where other companies' raw materials are also being used. The information provided by us does not absolve the user from the obligation of investigating the possibility of infringement of third parties' rights and, if necessary, clarifying the position. Recommendations for use do not constitute a warranty, either express or implied, of the fitness or suitability of the product for a particular purpose.