

SEMICOSIL[®] M3E

Silanes

SEMICOSIL[®] M3E is Methyltriethoxysilane of high purity.

Empirical formula $C_7H_{18}O_3Si$ CAS No.: 2031-67-6 | Molecular weight 178

Properties

- high purity
- low metal content
- low chloride content

Technical data

General Characteristics

Property	Condition	Value	Method
Appearance	-	colorless, clear liquid	ASTM D 624
Assay by Gas Chromatography	-	99.0 %	-
Boiling point	1013 hPa	143 °C	-
Density	25 °C	0.89 g/cm ³	DIN 51757
Melting point	-	< -40 °C	-
Refractive index	-	1.3805 - 1.3815	-
Solubility	-	Soluble in most common organic solvents g/l	-

These figures are only intended as a guide and should not be used in preparing specifications.

All the information provided is in accordance with the present state of our knowledge. Nonetheless, we disclaim any warranty or liability whatsoever and reserve the right, at any time, to effect technical alterations. The information provided, as well as the product's fitness for an intended application, should be checked by the buyer in preliminary trials. Contractual terms and conditions always take precedence. This disclaimer of warranty and liability also applies particularly in foreign countries with respect to third parties' rights.

Applications

- Silanes for chemical vapor deposition (CVD) and spin-on dielectrics (SOD)

Application details

SEMICOSIL® M3E was developed for the semiconductor industry, e.g. as precursor for low dielectric constant interlayer dielectrics.

Packaging and storage

Storage

The 'Best use before end' date of each batch is shown on the product label. Storage beyond the date specified on the label does not necessarily mean that the product is no longer usable. In this case however, the properties required for the intended use must be checked for quality assurance reasons.

Safety notes

Comprehensive instructions are given in the corresponding Material Safety Data Sheets. They are available on request from WACKER subsidiaries or may be printed via WACKER web site <http://www.wacker.com>.

QR Code SEMICOSIL® M3E



For technical, quality or product safety questions, please contact:

Wacker Chemie AG, Hanns-Seidel-Platz 4, 81737 Munich, Germany
productinformation@wacker.com, www.wacker.com

The data presented in this medium are in accordance with the present state of our knowledge but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this medium should be checked by preliminary trials because of conditions during processing over which we have no control, especially where other companies' raw materials are also being used. The information provided by us does not absolve the user from the obligation of investigating the possibility of infringement of third parties' rights and, if necessary, clarifying the position. Recommendations for use do not constitute a warranty, either express or implied, of the fitness or suitability of the product for a particular purpose.