

# DEHESIVE<sup>®</sup> 906 AMA<sup>®</sup>



## Vinylpolymers

DEHESIVE<sup>®</sup> 906 AMA<sup>®</sup> is a solvent-free, addition-curing silicone intended for coating paper and other substrates.

## Properties

- fast, low temperature cure
- low level of silicone mist at high coating speeds
- low release at low peel speeds
- medium release at high peel speeds
- good coverage at low silicone coat weights
- suitable for coating PP and PE films and PE-coated paper

## Specific features

- Polymer
- Solvent-free

## Technical data

### General Characteristics

Property	Condition	Value	Method
Viscosity, dynamic	25 °C	approx. 210 mPa·s	-
Content of active agent	-	100.0 %	-
Appearance	-	colorless	WSTM 2298
Density	25 °C	0.97 g/cm <sup>3</sup>	DIN 51757

These figures are only intended as a guide and should not be used in preparing specifications.

All the information provided is in accordance with the present state of our knowledge. Nonetheless, we disclaim any warranty or liability whatsoever and reserve the right, at any time, to effect technical alterations. The information provided, as well as the product's fitness for an intended application, should be checked by the buyer in preliminary trials. Contractual terms and conditions always take precedence. This disclaimer of warranty and liability also applies particularly in foreign countries with respect to third parties' rights.

## Applications

- Release Coatings

## Application details

DEHESIVE® 906 AMA® is part of a multicomponent release coating to produce paper and filmic release liners. The liners are used for production of single and double-sided industrial laminates.

### Mixing order:

1. First pour in CRA® modifier in case CRA® is used.
2. Add DEHESIVE® 906 AMA® in several portions and stir slowly until the mixture is homogeneous .
3. Thoroughly stir in crosslinker homogeneously.
4. Slowly stir in catalyst homogeneously and avoid local over concentrations.

Make sure that catalyst poisons are avoided in batch preparation and processing steps.

For a short time compounded batches may emit small amounts of hydrogen. To avoid pressure formation store in ventilated containers.

### Coating :

Modern coating systems are particularly effective with DEHESIVE® systems. The batch is best added directly to the nip of the coating unit.

## Packaging and storage

### Storage

The 'Best use before end' date of each batch is shown on the product label. Storage beyond the date specified on the label does not necessarily mean that the product is no longer usable. In this case however, the properties required for the intended use must be checked for quality assurance reasons.

## Safety notes

Comprehensive instructions are given in the corresponding Material Safety Data Sheets. They are available on request from WACKER subsidiaries or may be printed via WACKER web site <http://www.wacker.com>.

## QR Code DEHESIVE® 906 AMA®



### For technical, quality or product safety questions, please contact:

**Wacker Chemie AG**, Hanns-Seidel-Platz 4, 81737 Munich, Germany  
[productinformation@wacker.com](mailto:productinformation@wacker.com), [www.wacker.com](http://www.wacker.com)

The data presented in this medium are in accordance with the present state of our knowledge but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this medium should be checked by preliminary trials because of conditions during processing over which we have no control, especially where other companies' raw materials are also being used. The information provided by us does not absolve the user from the obligation of investigating the possibility of infringement of third parties' rights and, if necessary, clarifying the position. Recommendations for use do not constitute a warranty, either express or implied, of the fitness or suitability of the product for a particular purpose.