

ELASTOSIL[®] R 573/70 A/B



High Consistency Silicone Rubber (HCR)

ELASTOSIL[®] R 573/70 A/B is a two component, electrically conductive HCR silicone rubber for the manufacture of electrically conductive products.

Properties

This product is an addition cured electrically conductive HCR silicone rubber which shows a low volume resistivity.

This product can be used within a temperature range of - 55 °C to + 210 °C.

Specific features

- Addition Curing
- Electrically conductive
- Two-component

Technical data

Properties Cured

Cure conditions: 15 min / 165 °C in press, post-cured 30 min / 200 °C

Property	Condition	Value	Method
Appearance	-	black	-
Hardness Shore A	-	71	DIN ISO 48-4
Density	-	1.16 g/cm ³	DIN EN ISO 1183-1 A
Tensile strength	-	6.2 N/mm ²	ISO 37 type 1
Elongation at break	-	246 %	ISO 37 type 1
Tear strength	-	14 N/mm	ASTM D 624 B
Compression Set ⁽¹⁾	22 h 175 °C	29 %	DIN ISO 815-1 type B method A
Volume resistivity	-	1.6 Ohmcm	IEC 62631-3-1
Rebound resilience	-	49 %	ISO 4662

¹post-cured 0.5 h / 200 °C

These figures are only intended as a guide and should not be used in preparing specifications.

All the information provided is in accordance with the present state of our knowledge. Nonetheless, we disclaim any warranty or liability whatsoever and reserve the right, at any time, to effect technical alterations. The information provided, as well as the product's fitness for an intended application, should be checked by the buyer in preliminary trials. Contractual terms and conditions always take precedence. This disclaimer of warranty and liability also applies particularly in foreign countries with respect to third parties' rights.

Applications

- Ignition & Battery Cables
- Molded Parts
- Profiles & Tubings

Application details

Electrically conductive profiles, EMI-gaskets, ignition cables (core), band electrodes

Processing

ELASTOSIL® R 573/70 A/B is delivered as A- & B-component system.

ELASTOSIL® R 573/70 A/B are homogeneously mixed in a ration of 1 : 1. Care must be taken to keep the compound cool during mixing. Crosslinking begins when mixing both components together. The rate and degree of crosslinking depends on the storage time and temperature. At 23 °C the mixture has a pot life of about 24 h. This can be extended by storing the catalyzed mixture at a lower temperature.

A homogeneous mixture is a must, but please avoid temperatures >30 °C along the mixing process in order to maintain best processing behavior.

For detailed information please refer to the latest edition of our brochure "SOLID AND LIQUID SILICONE RUBBER - MATERIAL AND PROCESSING GUIDELINES".

Packaging and storage

Packaging

This product is available in 20 kg cardboard packaging.

Special delivery forms are possible but depend on several technical and commercial aspects. Please contact your local sales manager in such cases.

Storage

Once opened, cardboard boxes should always be resealed after use to prevent the platinum catalyst from being poisoned by amines, sulphur or phosphorus compounds. The 'Best use before end' date of each batch is shown on the product label. Storage beyond the date specified on the label does not necessarily mean that the product is no longer usable. In this case however, the properties required for the intended use must be checked for quality assurance reasons.

Safety notes

Comprehensive instructions are given in the corresponding Material Safety Data Sheets. They are available on request from WACKER subsidiaries or may be printed via WACKER web site <http://www.wacker.com>.

QR Code ELASTOSIL® R 573/70 A/B



For technical, quality or product safety questions, please contact:

Wacker Chemie AG, Hanns-Seidel-Platz 4, 81737 Munich, Germany
productinformation@wacker.com, www.wacker.com

The data presented in this medium are in accordance with the present state of our knowledge but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this medium should be checked by preliminary trials because of conditions during processing over which we have no control, especially where other companies' raw materials are also being used. The information provided by us does not absolve the user from the obligation of investigating the possibility of infringement of third parties' rights and, if necessary, clarifying the position. Recommendations for use do not constitute a warranty, either express or implied, of the fitness or suitability of the product for a particular purpose.