

# NEXIVA® 928

## Dispersible Polymer Powders

NEXIVA® GP 928 is a flexible dispersible polymer powder based on vinyl acetate, vinyl chloride and ethylene. It is designed as a general binder for a variety of applications in various industries including but not limited to adhesives.

### Properties

NEXIVA® GP 928 provides the following advantages to the manufacturers:

- Biocide free binder.
- Allows the formulation of powder based products.
- No organic solvents, plasticizers, film forming agents need in formulations, due to low minimum film forming temperature.
- Easier storage, no silo in need
- Low odor.
- No skinning compared to liquid binders.
- Contain a fine mineral filler as an anti-blocking agent.
- Better workability in extreme climatic conditions.

## Technical data

### Specification

Property	Condition	Value	Method
Solids content	-	min. 98 %	DIN EN ISO 3251
Bulk density	-	450 - 650 kg/m <sup>3</sup>	DIN EN ISO 60
Particle size (%)	> 400 µm	max. 4 %	DIN EN ISO 4610

### General Characteristics

Property	Condition	Value	Method
Appearance	-	white to light beige powder	Visual
Minimum film forming temperature	-	5 °C	DIN ISO 2115

These figures are only intended as a guide and should not be used in preparing specifications.

All the information provided is in accordance with the present state of our knowledge. Nonetheless, we disclaim any warranty or liability whatsoever and reserve the right, at any time, to effect technical alterations. The information provided, as well as the product's fitness for an intended application, should be checked by the buyer in preliminary trials. Contractual terms and conditions always take precedence. This disclaimer of warranty and liability also applies particularly in foreign countries with respect to third parties' rights.

## Application details

NEXIVA® GP 928 is recommended as binder for various applications for example liquid or powder based adhesives, due to its adequate binding power and good re-dispersibility in water.

### Processing

For the production of dry products, NEXIVA® GP 928 can be mixed into the dry mixture. For the production of ready-to-use adhesives, we recommend adding NEXIVA® directly to the mill base, just as is the case with the filler. After the powder is mixed with water, it should ideally be applied immediately. It may be necessary to add biocides to the water-mixed powder if the powder has not been used for a prolonged period of time before application.

## Packaging and storage

### Packaging

25 kg paper bags

### Storage

During storage, protect the product from contact with moisture. Prolonged storage at temperatures above 30 °C, especially in combination with pressure, humidity or exposure to sunlight, may result in blocking. Carefully seal any open containers and store them under suitable conditions. We recommend storing the product in a warehouse that provides cool and dry conditions. Do not store the product for more than six months, starting from the date at which it was received, unless the Certificate of Analysis contains a different date, which would take precedence. If the product is stored longer than recommended, it may still be used but users are advised to verify the properties required for the intended use.

## Safety notes

Comprehensive instructions are given in the corresponding Material Safety Data Sheets. These are available on request from WACKER sales offices or may be downloaded from the WACKER Web site [www.wacker.com/nexiva](http://www.wacker.com/nexiva).

## QR Code NEXIVA® 928



### For technical, quality or product safety questions, please contact:

**Wacker Chemie AG**, Hanns-Seidel-Platz 4, 81737 Munich, Germany  
[productinformation@wacker.com](mailto:productinformation@wacker.com), [www.wacker.com](http://www.wacker.com)

The data presented in this medium are in accordance with the present state of our knowledge but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this medium should be checked by preliminary trials because of conditions during processing over which we have no control, especially where other companies' raw materials are also being used. The information provided by us does not absolve the user from the obligation of investigating the possibility of infringement of third parties' rights and, if necessary, clarifying the position. Recommendations for use do not constitute a warranty, either express or implied, of the fitness or suitability of the product for a particular purpose.