

WACKER® AF 21 BR

Functional Silicone Fluids

WACKER® AF 21 is a premium modified amino functional fluid.

Properties

WACKER® AF 21 yields an extremely soft hand with little to no shade change most notably yellowing due to normal textile processes. WACKER® AF 21 gives a less hydrophobizing effect on natural fibers than standard amino softeners. WACKER® AF 21 will also give some wrinkle recovery and improved fabric elasticity.

Technical data

General Characteristics

Property	Condition	Value	Method
Amine number	-	0.16 - 0.22 meq/g	-
Viscosity	25 °C	1000 - 10000 mPa·s	DIN 53019
Appearance	-	Transparent to yellow	Visual
Volatiles	5 g 1 h 100 °C	≤ 12 %	-

These figures are only intended as a guide and should not be used in preparing specifications.

All the information provided is in accordance with the present state of our knowledge. Nonetheless, we disclaim any warranty or liability whatsoever and reserve the right, at any time, to effect technical alterations. The information provided, as well as the product's fitness for an intended application, should be checked by the buyer in preliminary trials. Contractual terms and conditions always take precedence. This disclaimer of warranty and liability also applies particularly in foreign countries with respect to third parties' rights.

Applications

- Fiber Finishing
- Textile Finishing
- Textiles & Leather

Application details

WACKER® AF 21 is particularly suitable as an active substance in non yellowing softener formulations for the impregnation of fibers and textiles. WACKER® AF 21 imparts a very soft and drapable handle to woven and knitted fabrics.

WACKER® AF 21 improves the wash-and-wear properties and the crease recovery angle, sewability and reduces abrasion loss. The effects are fast to washing and dry cleaning. WACKER® AF 21 has no effect on the degree of white in a softener formulation when usual application conditions are adhered to. As a rule no adverse effect on the shade or color fastness properties of colored goods is observed.

Processing:

WACKER® AF 21 can be applied from solution, or emulsion. Suitable solvents are aliphatic and aromatic hydrocarbons, chlorinated hydro-carbons, esters, higher alcohols, and ketones. Most textile processes are water based.

Hence WACKER® AF 21 is mainly applied from emulsion. WACKER® AF 21 is suitable for the formulation of micro emulsions and macro emulsions. Emulsions made with WACKER® AF 21 are diluted to the optimum concentration for the specific fabric. Application can be done by padding or exhaustion. WACKER® AF 21 can be utilized as the active substance in softener emulsions or in combination with other components, e.g. paraffin waxes, organic softeners, etc. Compatibility of the components has to be checked in each individual case. Typical Formulation 50.0 parts demineralized water 5.0 parts tridecyl alcohol 6EO 3.0 parts tridecyl alcohol 9EO 4.0 parts diethylene glycol monobutylether 20.0 parts WACKER® AF 21 17.9 parts demineralized water 0.1 parts conservation agents The emulsifier is dissolved in the demineralized water, then gradually add WACKER® AF 21 and mix until the product is clear and homogenous. Finally, the second amount of water and conservation agent are added.

Packaging and storage

Packaging

- 0,95 kg bottle
- 190 kg drum
- 950 kg IBC

Storage

The "Best use before end date" of each batch is shown on the Certificate of Analysis. Storage beyond the date specified on the Certificate of Analysis does not necessarily mean that the product is no longer usable. In this case however, the properties required for the intended use must be checked for quality assurance reasons

Safety notes

Comprehensive instructions are given in the corresponding Material Safety Data Sheets. They are available on request from WACKER subsidiaries or may be printed via WACKER web site <http://www.wacker.com>.

QR Code WACKER® AF 21 BR



For technical, quality or product safety questions, please contact:

Wacker Chemie AG, Gisela-Stein-Strasse 1, 81671 Munich, Germany
productinformation@wacker.com, www.wacker.com

The data presented in this medium are in accordance with the present state of our knowledge but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this medium should be checked by preliminary trials because of conditions during processing over which we have no control, especially where other companies' raw materials are also being used. The information provided by us does not absolve the user from the obligation of investigating the possibility of infringement of third parties' rights and, if necessary, clarifying the position. Recommendations for use do not constitute a warranty, either express or implied, of the fitness or suitability of the product for a particular purpose.