

WACKER® FINISH CT 95 E

Functional Silicone Fluids

WACKER® FINISH CT 95 E is a non-ionic micro emulsion of an amino functional silicone fluid.

Properties

WACKER® FINISH CT 95 E is particularly suitable as softener for the impregnation of fibers and textiles.

WACKER® FINISH CT 95 E imparts a very soft, smooth and elastic touch to woven and knitted fabrics.

WACKER® FINISH CT 95 E is considered to be the best softening agent for woolen goods and PES knitware.

WACKER® FINISH CT 95 E improves the wash-and-wear properties the crease recovery angle and tear strength and reduces abrasion loss. The effects are fast to washing and dry cleaning.

Specific features

- Dilutable with water
- Low VOC

Technical data

General Characteristics

Property	Condition	Value	Method
Solid content	-	approx. 25 %	Microwave oven
pH-Value	-	approx. 5	-
Appearance	-	clear, opaque	-
Ionogenity	-	nonionic	-

These figures are only intended as a guide and should not be used in preparing specifications.

All the information provided is in accordance with the present state of our knowledge. Nonetheless, we disclaim any warranty or liability whatsoever and reserve the right, at any time, to effect technical alterations. The information provided, as well as the product's fitness for an intended application, should be checked by the buyer in preliminary trials. Contractual terms and conditions always take precedence. This disclaimer of warranty and liability also applies particularly in foreign countries with respect to third parties' rights.

Applications

- Softeners & Hydrophilic Softeners
- Textile & Leather
- Textile Finishing

Application details

Processing:

WACKER® FINISH CT 95 E gives permanent effects even without the addition of a catalyst. Specific curing conditions need not be adhered to if no resins are used.

WACKER® FINISH CT 95 E can be applied either by padding or by the exhaust method but the finishing liquors should not be subjected to high shear as this might cause instability.

5 - 30 g/l WACKER® FINISH CT 95 E are recommended for the pad method. For the exhaust method 1 - 3 %, relative to the weight of goods are adequate and the treatment should be carried out at 40 - 50 °C for 15 - 20 minutes. The pH of the liquor should not exceed pH 5. It may need to be adjusted with acetic acid.

WACKER® FINISH CT 95 E can be applied either alone or together with resins and other finishing agents.

If WACKER® FINISH CT 95 E is used together with crosslinking agents and other additives, it should be added, in dilute form, after all the other products. (This recommendation applies generally to the processing of all polysiloxanes).

Higher crease recovery angles and lower abrasion values can be obtained in resin finishes by using WACKER® FINISH CT 95 E. A wide range of handles can be obtained by combining WACKER® FINISH CT 95 E with conventional softening agents and other additives.

Typical recipes:

Woven and knitted materials from synthetic fibres:

0.5 ml/l acetic acid 60 %
10 - 30 g/l WACKER® FINISH CT 95 E
pad, liquor pick-up about 50 %, dry at 120 - 150 °C.

Single jersey or interlock cotton fabrics (exhaust method):

0.5 ml/l acetic acid 60 %
2 - 4 g/l WACKER® FINISH CT 95 E

10 - 30 minutes at 30 - 40 °C without rinsing, hydroextract dry at 100 - 150 °C.

Packaging and storage

Packaging

- 0,5 kg bottle
- 145 kg drum
- 950 kg IBC

Storage

The 'Best use before end' date of each batch is shown on the product label.

Storage beyond the date specified on the label does not necessarily mean that the product is no longer usable. In this case however, the properties required for the intended use must be checked for quality assurance reasons.

Emulsions showing signs of creaming should be agitated before use to assure uniform consistency.

Safety notes

Comprehensive instructions are given in the corresponding Material Safety Data Sheets. They are available on request from WACKER subsidiaries or may be printed via WACKER web site <http://www.wacker.com>.

QR Code WACKER® FINISH CT 95 E



For technical, quality or product safety questions, please contact:

Wacker Chemie AG, Hanns-Seidel-Platz 4, 81737 Munich, Germany
productinformation@wacker.com, www.wacker.com

The data presented in this medium are in accordance with the present state of our knowledge but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this medium should be checked by preliminary trials because of conditions during processing over which we have no control, especially where other companies' raw materials are also being used. The information provided by us does not absolve the user from the obligation of investigating the possibility of infringement of third parties' rights and, if necessary, clarifying the position. Recommendations for use do not constitute a warranty, either express or implied, of the fitness or suitability of the product for a particular purpose.