

WACKER® TN

Functional Silicone Fluids

WACKER® TN is a modified silicone fluid of medium viscosity whose special chemical structure imbues it with the benefits of silicone fluids and mineral oils.

WACKER® TN is used for the formulation of release agents for thermal molding of rubber, plastics and low-melting nonferrous metals. It is superior to conventional silicone fluids when the finished parts are subsequently to be painted, printed, coated or bonded. An outstanding release effect is even obtained when extremely small amounts of the release agent are used. The result is an easy, accurate reproduction of every surface detail of the molded article. WACKER® TN exhibits excellent film forming properties.

Technical data

General Characteristics

Property	Condition	Value	Method
Viscosity, kinematic	25 °C	approx. 1300 mm ² /s	DIN 53019
Refractive index	-	approx. 1.463	DIN 51423
Appearance	-	clear, colorless	-
Color Index	-	0 - 50	-
Melting point	-	-22 °C	-
Volatility	5 g 2 h 230 °C	0.0 - 1.5 %	-
melting point	-	-22 °C	-

These figures are only intended as a guide and should not be used in preparing specifications.

All the information provided is in accordance with the present state of our knowledge. Nonetheless, we disclaim any warranty or liability whatsoever and reserve the right, at any time, to effect technical alterations. The information provided, as well as the product's fitness for an intended application, should be checked by the buyer in preliminary trials. Contractual terms and conditions always take precedence. This disclaimer of warranty and liability also applies particularly in foreign countries with respect to third parties' rights.

Applications

- Antifriction Agents & Lubricants
- Car Care
- Light Alloy Diecasting
- Polyurethane Processing

Application details

For easy application, WACKER® TN may be diluted with solvents such as white spirit. To ensure optimum flow, maximum number of moldings and economic use of the release agent, it is advisable to carry out preliminary tests to ascertain the optimum concentration, type of solvent, method of application and mold temperature. Generally, solutions with a silicone content of approximately 1 % are best to start with.

Packaging and storage

Storage

The 'Best use before end' date of each batch is shown on the product label. Storage beyond the date specified on the label does not necessarily mean that the product is no longer usable. In this case however, the properties required for the intended use must be checked for quality assurance reasons.

Safety notes

Comprehensive instructions are given in the corresponding Material Safety Data Sheets. They are available on request from WACKER subsidiaries or may be printed via WACKER web site <http://www.wacker.com>.

QR Code WACKER® TN



For technical, quality or product safety questions, please contact:

Wacker Chemie AG, Gisela-Stein-Strasse 1, 81671 Munich, Germany
productinformation@wacker.com, www.wacker.com

The data presented in this medium are in accordance with the present state of our knowledge but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this medium should be checked by preliminary trials because of conditions during processing over which we have no control, especially where other companies' raw materials are also being used. The information provided by us does not absolve the user from the obligation of investigating the possibility of infringement of third parties' rights and, if necessary, clarifying the position. Recommendations for use do not constitute a warranty, either express or implied, of the fitness or suitability of the product for a particular purpose.