

ELASTOSIL[®] RT 646 A/B



Room Temperature Curing Silicone Rubber (RTV-2)

ELASTOSIL[®] RT 646 A/B is a castable, addition-curing, two-component silicone rubber which vulcanizes at room temperature.

Main applications: Moldmaking, encapsulation of electronic components, all-round potting compound.

Properties

- High hardness and good mechanical properties
- Good chemical resistance
- Good resistance to casting resins
- Excellent reversion resistance
- Fast and non-shrink vulcanization at room temperature
- Vulcanization can be accelerated considerably by heat

Specific features

- Addition Curing
- Flowable
- Resistance against casting resins
- Two-component

Technical data

Properties Uncured

Property	Condition	A	B	Method
Color	-	beige	transparent	-
Density	-	1.3 g/cm ³	1.01 g/cm ³	DIN EN ISO 2811-1
Viscosity, dynamic	23 °C	110000 mPa·s	2000 mPa·s	ISO 3219
Platinum catalyst in component	-	A	-	-

These figures are only intended as a guide and should not be used in preparing specifications.

Properties Catalyzed A+B

Property	Condition	Value	Method
Viscosity, dynamic of mix	-	70000 mPa·s	ISO 3219
Mix ratio ⁽¹⁾	-	10 : 1	A : B
Pot Life up to 100000 mPa s	23 °C	80 min	DIN EN ISO 2555
Linear shrinkage (curing at room temperature)	-	≤ 0.1 %	-

⁽¹⁾(pbw)

These figures are only intended as a guide and should not be used in preparing specifications.

Properties Cured

Cured for 60 min at 150 °C in a circulating air oven.

Property	Condition	Value	Method
Color	-	beige	-
Density	23 °C	1.28 g/cm ³	DIN EN ISO 1183-1 A
Tear strength	-	12 N/mm	ASTM D 624 B
Hardness Shore A	-	53	DIN ISO 48-4
Tensile strength	-	5 N/mm ²	ISO 37 type 1
Elongation at break	-	280 %	ISO 37 type 1

These figures are only intended as a guide and should not be used in preparing specifications.

All the information provided is in accordance with the present state of our knowledge. Nonetheless, we disclaim any warranty or liability whatsoever and reserve the right, at any time, to effect technical alterations. The information provided, as well as the product's fitness for an intended application, should be checked by the buyer in preliminary trials. Contractual terms and conditions always take precedence. This disclaimer of warranty and liability also applies particularly in foreign countries with respect to third parties' rights.

Applications

- Reproduction Molding

Application details

- Encapsulation of electronic components
- All-round potting compound
- Mold making

Processing

Important note:

The platinum catalyst is in **component A**.

Caution:

Only components A and B with the same lot number may be processed together!

Temperature	Curing time, thickness 1 cm
23 °C	24 h
50 °C	60 min
100 °C	10 min
150 °C	5 min

To ensure homogeneity of the material, the components must be stirred thoroughly before they are removed or processed in their containers, in order to uniformly disperse any filler that might have settled during storage.

Please check also our brochures and info sheets.

Packaging and storage

Storage

The 'Best use before end' date of each batch is shown on the product label.

Storage beyond the date specified on the label does not necessarily mean that the product is no longer usable. In this case however, the properties required for the intended use must be checked for quality assurance reasons.

Safety notes

Comprehensive instructions are given in the corresponding Material Safety Data Sheets. They are available on request from WACKER subsidiaries or may be printed via WACKER web site <http://www.wacker.com>.

QR Code ELASTOSIL® RT 646 A/B



For technical, quality or product safety questions, please contact:

Wacker Chemie AG, Hanns-Seidel-Platz 4, 81737 Munich, Germany
productinformation@wacker.com, www.wacker.com

The data presented in this medium are in accordance with the present state of our knowledge but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this medium should be checked by preliminary trials because of conditions during processing over which we have no control, especially where other companies' raw materials are also being used. The information provided by us does not absolve the user from the obligation of investigating the possibility of infringement of third parties' rights and, if necessary, clarifying the position. Recommendations for use do not constitute a warranty, either express or implied, of the fitness or suitability of the product for a particular purpose.