

**WACKER**

CREATING TOMORROW'S SOLUTIONS

ELASTOSIL®

SEMICOSIL®

PRODUCT OVERVIEW

# INDUSTRIAL SEALING & BONDING APPLICATIONS

Non-slump RTV silicone grades (self-adhesive)

Main characteristics Brand / Product	Product type / curing system	Shrink-free curing	By-product of curing	Additional features	Food compliance	Viscosity [mPa·s]	Potlife or skin forming time	Hardness [Shore A]	Tensile strength [MPa]	Elongation at break [%]	Tear strength [N/mm]	Density, cured [g/cm <sup>3</sup> ]	Recommended max. service temperature [°C]	CIPG	FIPG	Aspect / color
<b>Self-adhesive after curing at room temperature</b>																
<b>General purpose</b>																
ELASTOSIL® E 4	RTV-1 / condensation cure		Acetic acid			Non-slump	20 min	15	2.0	750	7.3	1.02	180	X	X	Translucent
ELASTOSIL® E 43 N	RTV-1 / condensation cure		Acetic acid	Titanium catalyzed	X	300,000	5 min	30	7.8	450	12.5	1.12	180		X	Translucent / white / black
ELASTOSIL® E 900	RTV-1 / condensation cure		Acetic acid			Non-slump	10 min	20	0.6	300	4.2	1.02	230		X	Anthracite
ELASTOSIL® N 2199	RTV-1 / condensation cure		Alcohol			Non-slump	15 min	30	2.5	350	4.0	1.06	180		X	Translucent
ELASTOSIL® N 9111	RTV-1 / condensation cure		Alcohol	Titanium catalyzed		Non-slump	25 min	30	2.2	500	10.0	1.33	180		X	White / gray / black
ELASTOSIL® RT 771	RTV-2 / condensation cure (Base + Catalyst 10:1)*		Alcohol			150,000	5 min / 10 min *	45	1.0	180		1.54	180			Black
<b>Improved mechanical properties</b>																
ELASTOSIL® E 47	RTV-1 / condensation cure		Acetic acid			Non-slump	5 min	35	4.5	450	10.0	1.07	180		X	Translucent
<b>Heat resistance</b>																
ELASTOSIL®A 33	RTV-1 / condensation cure		Amine			Non-slump	10 min	28	2.5	300	7.8	1.17	200		X	Ivory
ELASTOSIL® E 14	RTV-1 / condensation cure		Acetic acid			Non-slump	15 min	38	3.0	450	7.0	1.18	250		X	Red
ELASTOSIL® E 43 N BLACK	RTV-1 / condensation cure		Acetic acid	Titanium catalyzed		300,000	5 min	30	7.5	500	12.5	1.12	250		X	Black
ELASTOSIL® RT 778	RTV-2 / condensation cure (Base + Catalyst 10:1)*		Alcohol	Fast cure		Non-slump	5 min / 10 min *	42	3.5	180	7.0	1.32	250		X	Black
<b>Media resistance</b>																
ELASTOSIL® N 2189	RTV-1 / condensation cure		Alcohol	Oil resistant		Non-slump	15 min	45	2.5	250	4.0	1.23	180		X	Black
ELASTOSIL® RT 779	RTV-2 / condensation cure (Base + Catalyst 10:1)**		Alcohol	Coolant resistant, oil resistant		Non-slump	5 min	50	2.8	250	9.5	1.32	180		X	Anthracite
<b>Compressible</b>																
ELASTOSIL® RT 773	RTV-2 / condensation cure (Base + Catalyst 10:1)*		Alcohol	Low density		Non-slump	5 min / 15 min *	35	0.7	75		0.70	140	X		Black
ELASTOSIL® SC 833	RTV-2 / platinum cure (A/B 1:1)		Hydrogen gas	Silicone foam, flame retardant		17,000	4 min	27	1.2	80		0.50	200	X		Black
ELASTOSIL® SC 835	RTV-2 / platinum cure (A/B 1:1)		Hydrogen gas	Silicone foam		15,000	240 s	20	0.45	80		0.45	200	X		Reddish brown
ELASTOSIL® SC 870	RTV-2 / platinum cure (A/B 1:1)		Hydrogen gas	Silicone foam, thixotropic		40,000	150 s	10	0.35	100		0.40	200	X		Gray
<b>Self-adhesive after curing at elevated temperature</b>																
<b>General purpose</b>																
ELASTOSIL® RT 703	1-component heat-curing / platinum cure	X		Screen printable		Non-slump	6 months	35	4.0	300		1.08	200	X	X	Translucent
ELASTOSIL® RT 724	RTV-2 / platinum cure (Base + Catalyst 10:1)***	X				100,000	12 h	45	4.0	180	10.0	1.25	180		X	Blue
SEMICOSIL® 986/1K	1-component heat-curing / platinum cure	X		UV fluorescent		Non-slump	6 months	51	5.0	200	8.0	1.07	180		X	Translucent
SEMICOSIL® 987 GR	1-component heat-curing / platinum cure	X		Sealing adhesive		Non-slump	6 months	50	5.0	200		1.10	180		X	Gray
SEMICOSIL® 988/1K gray	1-component heat-curing / platinum cure	X		Sealing adhesive		Non-slump	6 months	35	4.5	350	24.0	1.10	180	X	X	Gray
SEMICOSIL® 989/1K	1-component heat-curing / platinum cure	X		Sealing adhesive		Non-slump	6 months	55	5.0	200	10.0	1.10	180		X	Translucent
SEMICOSIL® 970 TC	RTV-2 / platinum cure (A/B 1:1)	X		Thermally conductive		94,000	16 h	65	4.0	90		2.26	160		X	White-gray
<b>High tear resistance</b>																
ELASTOSIL® RT 722	RTV-2 / platinum cure (A/B 1:1)	X		High tensile strength		Non-slump	6 h	45	6.0	300		1.10	180		X	Gray
<b>Heat resistance</b>																
ELASTOSIL® RT 702	1-component heat-curing / platinum cure	X				Non-slump	6 months	40	6.1	500	10.1	1.22	250		X	Black
<b>Media resistance</b>																
ELASTOSIL® RT 728	RTV-2 / platinum cure (A/B 1:1)	X		Coolant resistant		Non-slump	24 h	45	5.8	400	17.3	1.13	180	X		Anthracite
<b>Compressible</b>																
ELASTOSIL® RT 713	1-component heat-curing / platinum cure	X		Low density		Non-slump	6 months	23	1.5	350	7.0	0.75	140	X		Gray

\* base component to be combined with WACKER® Catalyst T 77 or WACKER® Catalyst T 77 PLUS (please see the corresponding technical data sheet for details)

\*\* base component to be combined with WACKER® Catalyst T 79 (please see the corresponding technical data sheet for details)

\*\*\* base component to be combined with ELASTOSIL® CAT PT, ELASTOSIL® CAT PT-F or ELASTOSIL® CAT UV to allow curing at room temperature, under heat or by UV light (please see the corresponding technical data sheet for details)



Note: these figures are intended as a guide and should not be used in preparing specifications.



**WACKER**

Wacker Chemie AG  
Hanns-Seidel-Platz 4  
81737 Munich, Germany  
[www.wacker.com/contact](http://www.wacker.com/contact)

[www.wacker.com](http://www.wacker.com)

Follow us on:   



7461B\_en/02.24 replaces 7461B\_e/02.19

The data presented in this medium are in accordance with the present state of our knowledge but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this medium should be checked by preliminary trials because of conditions during processing over which we have no control, especially where other companies' raw materials are also being used. The information provided by us does not absolve the user from the obligation of investigating the possibility of infringement of third parties' rights and, if necessary, clarifying the position. Recommendations for use do not constitute a warranty, either express or implied, of the fitness or suitability of the product for a particular purpose.