

WACKER

CREATING TOMORROW'S SOLUTIONS

VINNOL®

VINNAPAS®

NORTH AMERICAN PRODUCT PORTFOLIO

VINNAPAS® AND VINNOL® –
DISPERSIONS FOR NONWOVENS
AND TECHNICAL TEXTILES

BINDERS AND COATINGS FOR THE ENGINEERED FABRICS INDUSTRY

PRODUCT OVERVIEW

Grade	Polymer Base ²	Data ¹			Typical General Characteristics		Stabilization System		Grade
		Solids Content (Residue After Drying) [%]	Viscosity Brookfield [mPa.s]	pH	Glass Transition Temperature T _g (DSC) (Approx.) [°C]	Self-Crosslinking	Protective Colloid/Emulsifier System ³	Made Without Using APE-Containing Surfactants	
VINNAPAS® Vinyl Acetate-Ethylene Copolymer Dispersions									
VINNAPAS® EN 1165	VAc-E	52 ± 0.5	300 – 800	5.3 – 6.3	0	Yes	OS	Yes	VINNAPAS® EN 1165
VINNAPAS® EN 1267	VAc-E	52 ± 1	50 – 450	5.0 – 6.0	-15	Yes	OS	Yes	VINNAPAS® EN 1267
VINNAPAS® 192	VAc-E	52 ± 1	50 – 400	4.5 – 6.0	10	Yes	OS	Yes	VINNAPAS® 192
VINNAPAS® EP 1133	VAc-E	63 ± 1	800 – 1600	5.0 – 6.0	0	No	OS-PVOH	Yes	VINNAPAS® EP 1133
VINNAPAS® EZ 123	VAc-E	55 ± 1	100 – 800	4.7 – 5.7	17	No	OS-C	Yes	VINNAPAS® EZ 123
VINNOL® Vinyl Chloride Terpolymer Dispersions									
VINNOL® CE 35	VC-VAc-E	50 ± 1	40 – 100	6.0 – 7.5	36	No	OS	Yes	VINNOL® CE 35
VINNAPAS® Dispersible Polymers									
VINNAPAS® EP 907	VAc-E	55 ± 1	2,000 – 2,500	4.3 – 5.3	17	No	PVOH	Yes	VINNAPAS® EP 907

Grade	Product Properties					Application Methods				Grade
	Soft Hand	Firm Hand	Hydrophilic	Flame Retardant	Heat-Sealable	Impregnation	Print Bonding	Spraying	Foaming	
VINNAPAS® Vinyl Acetate-Ethylene Copolymer Dispersions										
VINNAPAS® EN 1165	●●		●●			●●	●●●	●●	●●	VINNAPAS® EN 1165
VINNAPAS® EN 1267	●●●		●●●			●●	●	●●●	●●	VINNAPAS® EN 1267
VINNAPAS® 192	●	●●	●●●			●●	●●	●●●	●●●	VINNAPAS® 192
VINNAPAS® EP 1133	●●	●	●●●		●●	●	●●●	●	●	VINNAPAS® EP 1133
VINNAPAS® EZ 123		●●	●●		●●●	●●	●●	●		VINNAPAS® EZ 123
VINNOL® Vinyl Chloride Terpolymer Dispersions										
VINNOL® CE 35		●●●	●	●●●	●●●	●●		●●	●●●	VINNOL® CE 35
VINNAPAS® Dispersible Polymers										
VINNAPAS® EP 907		●●●	●●		●●	●●	●	●		VINNAPAS® EP 907

¹ These figures are only intended as a guide and should not be used in preparing specifications.

² VAc = Vinyl acetate
E = Ethylene
VC = Vinyl chloride

³ PVOH = Poly(vinyl alcohol)
OS = Surface active agents
C = Cellulose derivative

●●● Very well suited
●● Well suited
● Suitable

WACKER

Wacker Chemical Corporation

6870 Tilghman Street
Allentown, PA 18106-9346
United States
Phone: +1 610 336-2700
info.usa@wacker.com

www.wacker.com

www.wacker.com/socialmedia



The data presented in this medium are in accordance with the present state of our knowledge but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this medium should be checked by preliminary trials because of conditions during processing over which we have no control, especially where other companies' raw materials are also being used. The information provided by us does not absolve the user from the obligation of investigating the possibility of infringement of third parties' rights and, if necessary, clarifying the position. Recommendations for use do not constitute a warranty, either express or implied, of the fitness or suitability of the product for a particular purpose.