



MOBILITY

e-NOVATION FOR FUEL CELLS POWERED BY SILICONES






USING SILICONES MEANS SEALING FOR LIFE

Silicones are used to seal fuel cells. The sealing functionality can be integrated into a cell component (bipolar plate or MEA/membrane electrode assembly) or can be pre-produced and added as an insert gasket during stacking.

Silicone gaskets are chemically inert, i.e. their properties remain stable in a fuel-cell set-up and during operation, and do not negatively affect the fuel-cell performance. They also achieve an excellent compression set, ensuring gas and coolant

tightness and thus securing the fuel cell against leakage over its full lifetime. In addition, silicone-based gaskets offer excellent thermal and degradation resistance. This combined effect maximizes the reliability of a fuel-cell power unit and extends its life and performance.

Silicones can be processed in various ways, including injection molding, screen printing, dispensing and bonding.



SILICONE MEANS ECONOMY AND FLEXIBILITY

Whether you are you looking for more quality, consistency, process robustness or improved productivity, or maybe a bonding process that combines all those advantages, WACKER has silicone-based solutions tailored to your process needs.



Injection Molding

Injection molding is used to apply a seal onto bipolar plates, the MEA (membrane electrode assembly) or separate metal or plastic gasket carriers, and allows complex and highly sophisticated seal geometry and topology solutions. Material supplied in drum or hobbock is processed in dosing and mixing equipment, and blended in a static mixer to a very homogeneous material.

Low Pressure Injection Molding

Low pressure molding can be classified as half-way between injection molding and potting. It is mainly used to form a molded-in-place gasket on the porous GDL (gas diffusion layer), with well-controlled saturation. Excellent mold flow, fast cure at low temperature are core material requirements for this process. As the process is much more gentle than conventional injection molding, it can be used for fragile GDL as well.

Screen Printing

Screen printing is a well established process in gasket manufacture. Silicone's well balanced rheology makes it a cost-effective candidate for the fast deposition of precise and homogeneous layers with thicknesses ranging from 30 µm up to 300 µm.

Dispensing

Dispensing is perfectly suited for prototyping or small series because it avoids expensive molds. In addition dispensing provides more flexibility in design and allows the use of a wide variety of materials. Dispensing is often the technology of choice in ramp-up scenarios.

A CHOICE OF RELIABLE SOLUTIONS

Benefit from WACKER's 70 years of silicone research to find a choice of reliable solutions tailored for every fuel-cell sealing application.

Both the MEA (membrane electrode assembly) and GDL (gas diffusion layer) are permanently exposed to hot-humid gas (hydrogen and air). Cured silicones therefore require moisture stability and chemical resistance to reactive intermediates of the electrochemical reaction which is essential for good long-term sealing properties. Thanks to their constant sealing properties over the full range of operating conditions of fuel cells, silicones are ideal sealing materials for this type of application.

ELASTOSIL® RT 624

- Excellent compression set
- Low viscosity and moderately shear thinning, ideal rheology for integrated seals in porous substrates by infiltration (GDL)
- Developed for direct contact to proton exchange membrane, catalyst layer and media supply
- Processing by low-pressure injection molding, dispensing or screen printing
- Low kick-off temperature (95 °C) avoids the drying-out of the proton exchange membrane
- 15 years of experience in automotive fuel-cell applications

ELASTOSIL® RT 621


- Screen-printing grade
- Pseudoplastic / shear thinning
- Good compression set
- Good media resistance under fuel-cell operation
- Suitable for contact to the catalyst layer and polymer electrolyte membrane (PEM)
- Designed for screen printing on bipolar plates, gasket or MEA framework

ELASTOSIL® LR 3003

- Injection molding/overmolding for integrated seals on bipolar plates, MEA
- Good media resistance
- Adhesion by use of Primer G 790
- Suitable for integrated seals on bipolar plates and gasket frameworks

ELASTOSIL® LR 3005 and LR 3025

- Injection molding grade for integrated seals
- Low compression set (non-post cure)
- Good general media resistance in fuel-cell conditions
- ELASTOSIL® LR 3025 especially for coolant contact, excellent stability versus radical-initiated degradation
- Low kick-off temperature
- Excellent mechanical properties
- Short cycle times
- Suitable for integrated seals on bipolar plates and gasket frameworks or manifolds



©ZBT Duisburg

PRODUCT OVERVIEW SILICONES FOR FUEL CELLS

Silicone Elastomers for Gaskets

Low compression set, excellent degradation resistance within fuel cell (temperature, acids, hydrogen, oxygen), no inhibition or contamination, low level of volatile siloxanes

Product	Process	Curing Mechanism	1 71	Viscosity D = 10 1/s [Pa⋅s] (ISO 2555)	Hardness Shore A DIN 53505	Tensile Strength [N/mm²] DIN 53 504-S1	Elongation at Break [%] DIN 53 504-S1	[N/mm]	Compression Set (22 h/175 °C) [%] DIN ISO 815-B	Color	UL Listing	Product
ELASTOSIL® RT 62 "4S"	Screen printing/ dispensing/low-pressure injection molding	Addition, heat curing	2-part, 1:1	40	40	5	300	> 14	< 5	Translucent	n.n.	ELASTOSIL® RT 62 "4S"
ELASTOSIL® LR 3005/30	Injection molding	Addition, heat curing	2-part, 1:1	130	30	6	610	18	15	Translucent	HB (1.5 mm)	ELASTOSIL® LR 3005/30
ELASTOSIL® LR 3005/40	Injection molding	Addition, heat curing	2-part, 1:1	390	40	7.8	610	22	16	Translucent	HB (1.5 mm)	ELASTOSIL® LR 3005/40
ELASTOSIL® LR 3005/50	Injection molding	Addition, heat curing	2-part, 1:1	320	50	9.4	520	24	14	Translucent	HB (1.5 mm)	ELASTOSIL® LR 3005/50
ELASTOSIL® LR 3005/60	Injection molding	Addition, heat curing	2-part, 1:1	450	60	10	400	29	13	Translucent	HB (1.5 mm)	ELASTOSIL® LR 3005/60
ELASTOSIL® LR 3025/40	Injection molding	Addition, heat curing	2-part, 1:1	150	40	6.5	600	18	8	Translucent	HB (1.5 mm)	ELASTOSIL® LR 3025/40
ELASTOSIL® RT 621	Screen printing	Addition, heat curing	2-part, 1:1	12	35	3	220	4	6	Translucent	n.n.	ELASTOSIL® RT 621

6 7





Wacker Chemie AG

Hanns-Seidel-Platz 4 81737 Munich, Germany www.wacker.com/contact

Follow us on: in









The data presented in this medium are in accordance with the present state of our knowledge but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this medium should be checked by preliminary trials because of conditions during processing over which we have no control, especially where other companies' raw materials are also being used. The information provided by us does not absolve the user from the obligation of investigating the possibility of infringement of third parties' rights and, if necessary, clarifying the position. Recommendations for use do not constitute a warranty, either express or implied, of the fitness or suitability of the product for a particular purpose.