

NORTH AMERICA | COATINGS | VINNAPAS® EP 8178 |
WEATHER RESISTIVE AIR BARRIER

VINNAPAS® EP 8178 – MODEL FORMULA

Model Weather-Resistant Air Barrier Formula with VINNAPAS® EP 8178			
Ingredients	Pounds	Gallons	Supplier
Grind			
Water	200.00	24.01	
Natrosol™ 250 MBR	5.25	0.45	Ashland
Ammonium Hydroxide, 28%	2.50	0.30	
Tamol™ 165	18.25	2.07	Dow Chemical
Drewplus™ TS-4481	1.10	0.14	Ashland
Nuosept® 95	2.00	0.21	Troy
Polyphase® 663	2.00	0.24	Troy
Ti-Pure™ R-706	57.50	1.73	Chemours
Minex® 3	525.00	24.19	Sibelco
Let-Down			
VINNAPAS® EP 8178	400.00	45.66	WACKER
Acrysol™ RM-12W	6.25	0.72	Dow Chemical
Drewplus™ TS-4481	1.50	0.19	Ashland
Water	2.00	0.24	
Total	1,223.35	100.16	
Paint Characteristics			
Density [lbs./gal.]	12.21		
Solids, by weight [%]	71.87		
Solids, by volume [%]	58.78		
VOC [g/L]	< 50		
PVC	44.03		
PVC/CPVC	0.77		

VINNAPAS® is a registered trademark of Wacker Chemie AG. Other trademarks are the property of their respective owners.



For technical, quality, or product safety questions, please contact:

Wacker Chemical Corp., 6870 Tilghman Street, Allentown, PA 18106-9346, USA

Phone: +1 610 336 2700, info.usa@wacker.com, www.wacker.com, www.wacker.com/socialmedia



The data presented in this medium are in accordance with the present state of our knowledge but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this medium should be checked by preliminary trials because of conditions during processing over which we have no control, especially where other companies' raw materials are also being used. The information provided by us does not absolve the user from the obligation of investigating the possibility of infringement of third parties' rights and, if necessary, clarifying the position. Recommendations for use do not constitute a warranty, either express or implied, of the fitness or suitability of the product for a particular purpose.