

BELSIL® SPR 45 VP



Silicone Resins (INCI)

BELSIL® SPR 45 VP is a solvent-free phenyl silicone resin. This product is produced for use as a film former in cosmetic applications.

INCI Polyphenylsilsesquioxane

Properties

BELSIL® SPR 45 VP combines the good film forming properties of silicone resins with high gloss and shine. Due to the high refractive index caused by the phenyl groups, BELSIL® SPR 45 VP provides up to 50 % higher gloss than standard silicone resins.

Technical data

General Characteristics

Property	Condition	Value	Method
Refractive index (film)	25 °C	1.569	-
Appearance	-	colorless flakes	-
INCI name	-	Polyphenylsilsesquioxane	-
Softening point	-	50 - 70 °C	-

These figures are only intended as a guide and should not be used in preparing specifications.

All the information provided is in accordance with the present state of our knowledge. Nonetheless, we disclaim any warranty or liability whatsoever and reserve the right, at any time, to effect technical alterations. The information provided, as well as the product's fitness for an intended application, should be checked by the buyer in preliminary trials. Contractual terms and conditions always take precedence. This disclaimer of warranty and liability also applies particularly in foreign countries with respect to third parties' rights.

Applications

- Eye Make-up
- Lip Make-up
- Nail Polish
- Skin Care
- Sun Care

Application details

These special properties predestine BELSIL® SPR 45 VP as a raw material for color cosmetics, skin care and sun care products.

Packaging and storage

Storage

Maximum temperature allowed during storage and transportation: 30 °C

The 'Best use before end' date of each batch is shown on the product label.

Storage beyond the date specified on the label does not necessarily mean that the product is no longer usable. In this case however, the properties required for the intended use must be checked for quality assurance reasons.

Safety notes

Comprehensive instructions are given in the corresponding Material Safety Data Sheets. They are available on request from WACKER subsidiaries or may be printed via WACKER web site <http://www.wacker.com>.

QR Code BELSIL® SPR 45 VP



For technical, quality or product safety questions, please contact:

Wacker Chemie AG, Gisela-Stein-Strasse 1, 81671 Munich, Germany
productinformation@wacker.com, www.wacker.com

The data presented in this medium are in accordance with the present state of our knowledge but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this medium should be checked by preliminary trials because of conditions during processing over which we have no control, especially where other companies' raw materials are also being used. The information provided by us does not absolve the user from the obligation of investigating the possibility of infringement of third parties' rights and, if necessary, clarifying the position. Recommendations for use do not constitute a warranty, either express or implied, of the fitness or suitability of the product for a particular purpose.