WACKER

POWERSIL[®] 440 MH

High Consistency Silicone Rubber (HCR)

POWERSIL[®] 440 MH is a ready-to-use, electrically conductive silicone rubber grade for all types of moulding applications.

Properties

Specific features

• Electrically conductive

Technical data

Properties Cured

| Property | Condition | Value | Method |
|---------------------|-----------|------------------------|---------------------|
| Appearance | - | black | - |
| Hardness Shore A | - | 42 | DIN ISO 48-4 |
| Density | - | 1.11 g/cm ³ | DIN EN ISO 1183-1 A |
| Tensile strength | - | 7.5 N/mm² | ISO 37 type 1 |
| Elongation at break | - | 500 % | ISO 37 type 1 |
| Tear strength | - | 12 N/mm | ASTM D 624 B |
| Volume resistivity | - | 30 Ohmcm | IEC 62631-3-1 |

These figures are only intended as a guide and should not be used in preparing specifications.

All the information provided is in accordance with the present state of our knowledge. Nonetheless, we disclaim any warranty or liability whatsoever and reserve the right, at any time, to effect technical alterations. The information provided, as well as the product's fitness for an intended application, should be checked by the buyer in preliminary trials. Contractual terms and conditions always take precedence. This disclaimer of warranty and liability also applies particularly in foreign countries with respect to third parties' rights.

Applications

Cable Accessories

Application details

• field grading for cable accessories other electrically conductive parts

Processing

POWERSIL[®] 440 MH can be easily processed like other standard HCR grades. A profitable processing is easygoing as POWERSIL[®] 440 MH is shipped ready-to-use.

Press-moulding and injection-moulding are suitable for crosslinking POWERSIL[®] 440 MH. After vulcanizing, post curing of the parts is highly recommended at a temperature of 200 °C. While post curing be careful to have sufficient ventilation.

Packaging and storage

Storage

The 'Best use before end' date of each batch is shown on the product label.

Storage beyond the date specified on the label does not necessarily mean that the product is no longer usable. In this case however, the properties required for the intended use must be checked for quality assurance reasons.

Safety notes

Comprehensive instructions are given in the corresponding Material Safety Data Sheets. They are available on request from WACKER subsidiaries or may be printed via WACKER web site http://www.wacker.com.

QR Code POWERSIL® 440 MH



For technical, quality or product safety questions, please contact:

Wacker Chemie AG, Hanns-Seidel-Platz 4, 81737 Munich, Germany productinformation@wacker.com, www.wacker.com

The data presented in this medium are in accordance with the present state of our knowledge but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this medium should be checked by preliminary trials because of conditions during processing over which we have no control, especially where other companies' raw materials are also being used. The information provided by us does not absolve the user from the obligation of investigating the possibility of infringement of third parties' rights and, if necessary, clarifying the position. Recommendations for use do not constitute a warranty, either express or implied, of the fitness or suitability of the product for a particular purpose.