

POWERSIL® GEL FC A/B

Silicone Gels

POWERSIL® GEL FC A/B is a pourable, addition-curing, two-component silicone mixture that vulcanizes at room temperature to a soft silicone gel. POWERSIL® GEL FC A/B shows a very fast curing behavior.

Properties

- two-part, 1 : 1 mixing ratio
- very low viscosity (uncured)
- very low hardness (silicone gel)
- transparent vulcanizate
- excellent mechanical damping properties
- non-bleeding gel

Specific features

- Specific Features: Fast curing

Technical data

Properties Uncured

Property	Condition	A	B	Method
Color	-	transparent	transparent	-
Viscosity, dynamic (10 s ⁻¹)	-	1000 mPa·s	1000 mPa·s	DIN EN ISO 3219

These figures are only intended as a guide and should not be used in preparing specifications.

Properties Catalyzed A+B

Property	Condition	Value	Method
Viscosity, dynamic of mix (10 s ⁻¹)	-	1000 mPa·s	DIN EN ISO 3219
Platinum catalyst in component	-	B	-
Mix ratio	-	1 : 1	A : B
Pot Life	23 °C	20 min	-
Curing time (thickness: 1cm)	23 °C	35 min	-
Curing time (thickness: 1cm)	50 °C	6 min	-
Curing time (thickness: 1cm)	100 °C	3 min	-

These figures are only intended as a guide and should not be used in preparing specifications.

Properties Cured

Cure conditions (A + B): 30 min / 150 °C in a circulating air oven.

Property	Condition	Value	Method
Color	-	transparent	-
Density	-	0.97 g/cm ³	DIN EN ISO 1183-1 A
Penetration (Hardness) ⁽¹⁾	-	180 1/10mm	DIN ISO 2137
Volume resistivity	-	10 ¹⁶ Ohmcm	IEC 62631-3-1
Permittivity	50 Hz	2.5	IEC 62631-2-1
Dissipation factor	50 Hz	2 x 10 ⁻⁴	IEC 62631-2-1
Dielectric strength	-	23 kV/mm	IEC 60243-1

¹150g cone / 60s penetration time

These figures are only intended as a guide and should not be used in preparing specifications.

All the information provided is in accordance with the present state of our knowledge. Nonetheless, we disclaim any warranty or liability whatsoever and reserve the right, at any time, to effect technical alterations. The information provided, as well as the product's fitness for an intended application, should be checked by the buyer in preliminary trials. Contractual terms and conditions always take precedence. This disclaimer of warranty and liability also applies particularly in foreign countries with respect to third parties' rights.

Applications

- Cable Accessories
- Insulators

Application details

- sealing of MV and HV cable joints
- LV easy-to-use cable joints
- castings and sealants of electrical equipment

Processing

Important:

The platinum catalyst is contained in component B. Only components A and B with the same lot number may be processed together.

Surface preparation:

All surfaces must be clean and free of contaminants that will inhibit the cure of POWERSIL® GEL FC A/B. Examples of inhibiting contaminants are sulfur containing materials, plasticizers, urethanes, amine containing materials and organometallic compounds especially organo-tin compounds. If a substrate's ability to inhibit curing is unknown, a small scale test should be run to determine compatibility.

Mixing:

The two components should be thoroughly mixed at a 1 : 1 ratio by weight or volume. To eliminate any air introduced during dispensing or trapped under components or devices a vacuum encapsulation is recommended. The reactivity can be adjusted within wide limits by adding Catalyst EP or Inhibitor PT 88 to suit the processing requirements of the particular application. Catalyst EP increases the reactivity of the gel with corresponding reduction or pot life and curing time. Further information is given in our leaflet "Catalyst EP/Inhibitor PT 88". If the gel is too soft and tacky, reducing the amount of component B will result in a harder, less tacky vulcanizate. The hardest formulation is achieved with a mixing ratio for A : B of roughly 1.5 : 1. We recommend running preliminary tests to optimize conditions for the particular application. Comprehensive processing instructions are given in our leaflet "Wacker RTV-2 Silicone RubberProcessing"

Pigmentation:

POWERSIL® GEL FC A/B can be pigmented by adding 1 - 4 % of an ELASTOSIL® FL pigment paste.

Curing:

Curing time of addition curing silicone rubber is highly dependent on temperature, size and heat sink properties of the component being potted.

Packaging and storage

Storage

The 'Best use before end' date of each batch is shown on the product label.

Storage beyond the date specified on the label does not necessarily mean that the product is no longer usable. In this case however, the properties required for the intended use must be checked for quality assurance reasons.

Safety notes

According to the latest findings, the addition-curing silicone rubber POWERSIL® GEL FC A/B contains neither toxic or corrosive substances which would require special handling precautions.

Comprehensive instructions are given in the corresponding Material Safety Data Sheets. They are available on request from WACKER subsidiaries or may be printed via WACKER web site <http://www.wacker.com>.

QR Code POWERSIL® GEL FC A/B



For technical, quality or product safety questions, please contact:

Wacker Chemie AG, Hanns-Seidel-Platz 4, 81737 Munich, Germany
info@wacker.com, www.wacker.com

The data presented in this medium are in accordance with the present state of our knowledge but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this medium should be checked by preliminary trials because of conditions during processing over which we have no control, especially where other companies' raw materials are also being used. The information provided by us does not absolve the user from the obligation of investigating the possibility of infringement of third parties' rights and, if necessary, clarifying the position. Recommendations for use do not constitute a warranty, either express or implied, of the fitness or suitability of the product for a particular purpose.