

SILRES[®] POWDER D



Silane Powders

SILRES[®] POWDER D is a water-redispersible silicone water-repellent in powder form and used as a highly efficient additive. SILRES[®] POWDER D acts as outstanding water repellent even at very low concentrations without affecting the water vapour permeability. SILRES[®] POWDER D contains a fine mineral filler as antiblocking agent.

Properties

- redispersible technology i.e. excellent mixability with water
- based on highly efficient silicones
- produced without the use of organic solvents

Technical data

General Characteristics

Property	Condition	Value	Method
Appearance	-	white to light beige powder	Visual
Bulk density	-	220 - 400 kg/m ³	DIN EN ISO 60
Protective colloid / emulsifier system	-	polyvinyl alcohol	-
Solidscontent	-	min. 96.5 %	-

These figures are only intended as a guide and should not be used in preparing specifications.

All the information provided is in accordance with the present state of our knowledge. Nonetheless, we disclaim any warranty or liability whatsoever and reserve the right, at any time, to effect technical alterations. The information provided, as well as the product's fitness for an intended application, should be checked by the buyer in preliminary trials. Contractual terms and conditions always take precedence. This disclaimer of warranty and liability also applies particularly in foreign countries with respect to third parties' rights.

Applications

- Mineral Renders & Plasters
- Powder Paints

Application details

SILRES® POWDER D is a high-quality specialty product for enhancing the water repellency and water resistance of non load-bearing precast concrete products or mineral construction material mixes, e.g. premixed plasters, joint mortars and powder paints.

Properly formulated products exhibit:

- low water absorption coefficients
- excellent droplet effect
- low soiling tendency
- durability

SILRES® POWDER D can be used in both dry powder and liquid systems.

To produce non load-bearing precast concrete products or mineral construction material mixes such as premixed plasters, joint mortars or powder paints mix SILRES® POWDER D with the other dry materials using suitable equipment.

Very good water repellency and durability can be achieved with 0.1-0.5% based on the dry weight.

After sufficient water has been added, mortars can be mixed by hand or machine. Since mixing by hand only generates low shear forces, it is best to allow the mixture to mature by leaving it to stand for 5 minutes, and then to stir it again.

Packaging and storage

Storage

SILRES® POWDER D should be stored in a cool place and protected against moisture.

The "Best use before end" date of each batch is shown on the product label. Storage beyond the date specified on the label does not necessarily mean that the product is no longer usable. In this case however, the properties required for the intended use must be checked for quality assurance reasons.

If the product is stored under pressure, in damaged or fairly long opened packaging, the powder can tend to caking.

Blends of SILRES® POWDER D with hydraulic binders, fillers and pigments have better storage stability because these substances prevent caking. However, blends of this type still have to be protected against humidity.

Safety notes

Comprehensive instructions are given in the corresponding Material Safety Data Sheets. They are available on request from WACKER subsidiaries or may be printed via WACKER web site <http://www.wacker.com>.

QR Code SILRES® POWDER D



For technical, quality or product safety questions, please contact:

Wacker Chemie AG, Hanns-Seidel-Platz 4, 81737 Munich, Germany
productinformation@wacker.com, www.wacker.com

The data presented in this medium are in accordance with the present state of our knowledge but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this medium should be checked by preliminary trials because of conditions during processing over which we have no control, especially where other companies' raw materials are also being used. The information provided by us does not absolve the user from the obligation of investigating the possibility of infringement of third parties' rights and, if necessary, clarifying the position. Recommendations for use do not constitute a warranty, either express or implied, of the fitness or suitability of the product for a particular purpose.