

# VINNAPAS® CA 5677



## Polymer Dispersions

VINNAPAS® CA 5677 is an aqueous polymer dispersion based on vinyl acetate and ethylene. VINNAPAS® CA 5677 is not produced with any added organic solvents, plasticizers or formaldehyde donors.

## Technical data

### Specification

Property	Condition	Value	Method
Solids content	-	55 - 57 %	DIN EN ISO 3251
Viscosity, dynamic	23 °C	150 - 1850 mPa·s	DIN EN ISO 2555
pH	-	3.5 - 5.0	DIN/ISO 976

## General Characteristics

Property	Condition	Value	Method
Density	-	approx. 1.07 g/cm <sup>3</sup>	ISO 2811
Frost resistance	-	protect from freezing	-
Predominant particle size	-	approx. 200 nm	specific method
Protective colloid / emulsifier system	-	APEO- free surfactants	-
Appearance of the dispersion film	-	clear, glossy	Visual
Glass transition temperature	-	approx. 10 °C	specific method

These figures are only intended as a guide and should not be used in preparing specifications.

All the information provided is in accordance with the present state of our knowledge. Nonetheless, we disclaim any warranty or liability whatsoever and reserve the right, at any time, to effect technical alterations. The information provided, as well as the product's fitness for an intended application, should be checked by the buyer in preliminary trials. Contractual terms and conditions always take precedence. This disclaimer of warranty and liability also applies particularly in foreign countries with respect to third parties' rights.

## Applications

- Automotive Carpet & Interior
- Needlefelt Carpet
- Tufted Broadloom Carpet
- Tufted Carpet Tiles

## Application details

### General

VINNAPAS® CA 5677 offers high dry strength, excellent absorbent properties and imparts medium/ firm hand. VINNAPAS® CA 5677 can be used for needle-felt carpets and in the precoat coatings that are applied in the production of tufted carpet backings.

### Special

VINNAPAS® CA 5677 can be applied by a number of different application methods including foaming (direct coating), pan coating, saturation and spraying. VINNAPAS® CA 5677 performs well on various fiber types including polypropylene, polyamide, cellulose, and polyester.

### Processing

VINNAPAS® CA 5677 can take high filler loads with calcium carbonate or aluminium trihydrate (ATH) for compounding. Surfactants can also be added to VINNAPAS® CA 5677 to improve penetration of the binder into the substrate and improve absorbency of the finished product. Effective surfactant levels are 0.5% to 1.0% on dispersion solids. The compatibility and efficacy should be checked by conducting a storage stability test.

### Polymer Dispersions

VINNAPAS® CA 5677 can be mixed with most VINNAPAS® and VINNOL® dispersions as well as with most anionic and/or nonionic aqueous polymer dispersions. Here too, the compatibility of the mixture should be tested by conducting a storage test.

### Thickening agents

We recommend alkali-swellable poly(acrylic acid) derivatives or products with neutral pH, e.g., those based on cellulose derivatives, poly(vinyl alcohol) or polyurethane. Their compatibility and efficacy should be evaluated.

### Additional information

If the product is used in applications other than those mentioned, the choice, processing and use of the product is the sole responsibility of the purchaser. All legal and other regulations must be complied with.

For questions concerning food contact status according the chapter 21 CFR (US FDA) and German BfR, please feel free to contact us.

Wacker Chemie AG Hanns-Seidel-Platz 4 D-81737 München Germany

## Packaging and storage

### Storage

When the dispersion is stored in tanks, proper storage conditions must be maintained. The product has a shelf life of 6 months starting from the date of receipt if stored in the original, unopened containers at temperatures between 5 and 30 °C. Any longer periods for the maximum storage period that may be described in the Certificate of Analysis which accompanies each shipment of the product, take preference over this suggestion in which case the time period stated in the Certificate of Analysis shall be solely authoritative. Iron or galvanized iron containers and equipment are not recommended. Corrosion could result in discoloration of the dispersion or blends made from it in further processing. We therefore recommend the use of containers and equipment made of ceramic, rubberized or enameled materials, appropriately finished stainless steel, or plastic (rigid PVC, polyethylene or polyester resin). As polymer dispersions may tend to superficial film formation, skins or lumps may be formed during storage or transportation. A filtration process is thus recommended prior to utilization of the product.

### Preservation for Transport, Storage and further Processing

The product is adequately preserved during transportation and storage if kept in the original, unopened containers. However, if it is transferred to storage tanks, the dispersion should be protected against microbial attack by adding a suitable preservative package.

Measures should also be taken to ensure cleanliness of the tanks and pipes. In unstirred tanks, a layer of preservative-containing water should be sprayed onto the surface of the dispersion to prevent the formation of unwanted skin and possible attack by microorganisms. The thickness of this water layer should be < 5 mm for low viscosity dispersions and up to 10–20 mm for high viscosity products. Proper procedures – periodic tank cleaning and sanitization – must be set up in order to prevent microbial attack. Contact your biocide representative/supplier for further plant hygiene recommendations. Measures should be taken to ensure that only clean air enters the tank when the dispersion is removed.

Finished products manufactured from polymer dispersions usually also require preservation. The type and scope of preservation will depend on the raw materials used and the anticipated sources of contamination. The compatibility with other components and the efficacy of the preservative should always be tested in the respective formulation. Preservative manufacturers will be able to advise you about the type and dosage of preservative required.

## Safety notes

Comprehensive instructions are given in the corresponding Material Safety Data Sheets. These are available on request from WACKER sales offices or may be downloaded from the WACKER Web site [www.wacker.com/vinnapas](http://www.wacker.com/vinnapas).

## QR Code VINNAPAS® CA 5677



**For technical, quality or product safety questions, please contact:**

**Wacker Chemie AG**, Hanns-Seidel-Platz 4, 81737 Munich, Germany  
productinformation@wacker.com, www.wacker.com

The data presented in this medium are in accordance with the present state of our knowledge but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this medium should be checked by preliminary trials because of conditions during processing over which we have no control, especially where other companies' raw materials are also being used. The information provided by us does not absolve the user from the obligation of investigating the possibility of infringement of third parties' rights and, if necessary, clarifying the position. Recommendations for use do not constitute a warranty, either express or implied, of the fitness or suitability of the product for a particular purpose.