

VINNAPAS® EF 575



Polymer Dispersions

VINNAPAS® EF 575 is a carboxylated, surfactant stabilized vinyl acetate-ethylene copolymer dispersion with a glass transition temperature (T_g) of 0 °C. It was developed as a versatile binder for use in a variety of applications including caulks, sealants, and mastics.

Properties

- Good adhesion to aluminum, galvanized and stainless steel, wood, FRP and PVC
- Manufactured without the use of alkylphenol ethoxylate (APEO) surfactants or defoamers
- Produced without the use of formaldehyde donors
- Compatible with other latex dispersions and water-based urethane dispersions
- Can be formulated with various pigments, fillers and thickeners
- Can be formulated to pass numerous industry standards including ASTM C 834 and UL 181A/B
- Can be formulated to pass ASTM C557

Technical data

Specification

Property	Condition	Value	Method
Solids content	-	54.0 - 56.0 %	specific method
Viscosity, dynamic	25 °C	200 - 850 mPa·s	specific method
pH	-	4.0 - 5.0	specific method

General Characteristics

Property	Condition	Value	Method
Density	-	1.07 g/cm ³	specific method
Predominant particle size	-	approx. 0.2 µm	specific method
Protective colloid / emulsifier system	-	anionic surfactants	-
Glass transition temperature	-	approx. 0 °C	DSC, specific method
Mechanical stability	-	excellent	specific method

These figures are only intended as a guide and should not be used in preparing specifications.

All the information provided is in accordance with the present state of our knowledge. Nonetheless, we disclaim any warranty or liability whatsoever and reserve the right, at any time, to effect technical alterations. The information provided, as well as the product's fitness for an intended application, should be checked by the buyer in preliminary trials. Contractual terms and conditions always take precedence. This disclaimer of warranty and liability also applies particularly in foreign countries with respect to third parties' rights.

Protect against frost.

Applications

- Mastics
- Patch & Repair Compounds
- Water-Based Caulks

Packaging and storage

Storage

When the dispersion is stored in tanks, proper storage conditions must be maintained. If stored in the original, unopened containers at cool (below 30 °C), but frost-free temperatures the product has a shelf life of 9 months from the date of manufacture. Any longer periods for the maximum storage period that may be described in the Certificate of Analysis which accompanies each shipment of the product, take preference over this suggestion in which case the time period stated in the Certificate of Analysis shall be solely authoritative. Iron or galvanized-iron equipment and containers are not recommended because the dispersion is slightly acidic. Corrosion may result in discoloration of the dispersion or its blends when further processed. Therefore, the use of containers and equipment made of ceramics, rubberized or enameled materials, appropriately finished stainless steel, or plastic (e.g. rigid PVC, polyethylene or polyester resin) is recommended. As polymer dispersions may tend to superficial film formation, skins or lumps may form during storage or transportation. Filtration is therefore recommended prior to utilization of the product.

Preservation for Transport, Storage and further Processing

The product is adequately preserved during transportation and storage if kept in the original, unopened containers. However, if it is transferred to storage tanks, the dispersion should be protected against microbial attack by adding a suitable preservative package. To maintain proper storage conditions appropriate measures should also be taken to ensure cleanliness of the tanks and pipes. In a storage tank in which the product is not stirred, it is advisable to contact your biocide representative/supplier. Proper procedures must be set up in order to prevent microbial attack between necessary periodic tank cleaning and sanitization. These procedures will vary, since loading and unloading practices in each storage situation will differ slightly. Finished products manufactured from polymer dispersions usually also require preservation. The type and scope of preservation will depend on the raw materials used and the anticipated sources of contamination. The compatibility with other components and the efficacy of the preservative should always be tested in the respective formulation. Preservative manufacturers will be able to advise you about the type and dosage of preservative required.

Safety notes

Comprehensive instructions are given in the corresponding Safety Data Sheets. These are available on request from WACKER sales offices or may be downloaded from the WACKER Web site www.wacker.com/vinnapas.

QR Code VINNAPAS® EF 575



For technical, quality or product safety questions, please contact:

Wacker Chemie AG, Hanns-Seidel-Platz 4, 81737 Munich, Germany
productinformation@wacker.com, www.wacker.com

The data presented in this medium are in accordance with the present state of our knowledge but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this medium should be checked by preliminary trials because of conditions during processing over which we have no control, especially where other companies' raw materials are also being used. The information provided by us does not absolve the user from the obligation of investigating the possibility of infringement of third parties' rights and, if necessary, clarifying the position. Recommendations for use do not constitute a warranty, either express or implied, of the fitness or suitability of the product for a particular purpose.