

WACKER® AP 500

Functional Silicone Fluids

WACKER® AP 500 Silicone fluid is a clear, colorless, and odorless polydimethylsiloxane with a high proportion of phenyl groups.

Applications

- Antifriction Agents & Lubricants

Application details

- heat transfer fluid - pressure transfer fluid - dielectric in capacitors and transformers - base fluid of heat resistant lubricants
For practical purposes, the useful temperature range of WACKER® AP 500 is between -35 °C and +200 °C. However, this presupposes that heat-stressing of the fluid occurs under "chemically pure" conditions. Even trace amounts of acids, alkalis, mineral oils, organometallic compounds, metal salts or metal oxides can seriously reduce the service life. The flash point of the silicone fluid may be changed by heat-stressing. It is therefore particularly important in open systems to check the flash point at least once a year and more often if operating conditions demand.

Packaging and storage

Storage

The 'Best use before end' date of each batch is shown on the product label. Storage beyond the date specified on the label does not necessarily mean that the product is no longer usable. In this case however, the properties required for the intended use must be checked for quality assurance reasons.

Safety notes

Comprehensive instructions are given in the corresponding Material Safety Data Sheets. They are available on request from WACKER subsidiaries or may be printed via WACKER web site <http://www.wacker.com>.

QR Code WACKER® AP 500



For technical, quality or product safety questions, please contact:

Wacker Chemie AG, Hanns-Seidel-Platz 4, 81737 Munich, Germany
info@wacker.com, www.wacker.com

The data presented in this medium are in accordance with the present state of our knowledge but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this medium should be checked by preliminary trials because of conditions during processing over which we have no control, especially where other companies' raw materials are also being used. The information provided by us does not absolve the user from the obligation of investigating the possibility of infringement of third parties' rights and, if necessary, clarifying the position. Recommendations for use do not constitute a warranty, either express or implied, of the fitness or suitability of the product for a particular purpose.