

# WACKER® APF 130 STAB

## Functional Silicone Fluids

WACKER® APF 130 STAB is a clear, brown colored polydimethylsiloxane with a high proportion of phenyl groups. It has particularly low volatility. WACKER® APF 130 STAB is specially stabilized and has a particularly good thermal stability.

## Technical data

### General Characteristics

Property	Condition	Value	Method
Viscosity, kinematic	25 °C	120 - 140 mm <sup>2</sup> /s	DIN 51562-1
Refractive index	25 °C	1.4930 - 1.5070	DIN 51423
Content HCl	-	0 - 2 ppm	direct titration
Appearance	-	clear, brown	-
Density	25 °C	approx. 1.06 g/cm <sup>3</sup>	-
Flash point	-	approx. 230 °C	ISO 2719
Ignition temperature (liquids)	-	> 400 °C	DIN 51794
Specific heat	25 °C	1.46 J/gK	-
Therm. expansion coefficient	-	0.00082 - 0.00085 mLmL <sup>-1</sup> K <sup>-1</sup>	-
Thermal conductivity	50 °C	0.14 W/m.K	-
Volatility	5 g   4 h   250 °C	0.0 - 1.0 %	-

These figures are only intended as a guide and should not be used in preparing specifications.

All the information provided is in accordance with the present state of our knowledge. Nonetheless, we disclaim any warranty or liability whatsoever and reserve the right, at any time, to effect technical alterations. The information provided, as well as the product's fitness for an intended application, should be checked by the buyer in preliminary trials. Contractual terms and conditions always take precedence. This disclaimer of warranty and liability also applies particularly in foreign countries with respect to third parties' rights.

## Application details

- heat transfer fluid
- pressure transfer fluid

For practical purposes, the useful temperature range of WACKER® APF 130 STAB is between -35 °C and +250 °C. However, this presupposes that heat-stressing of the fluid occurs under "chemically pure" conditions.

Even trace amounts of acids, alkalis, mineral oils, organometallic compounds, metal salts or metal oxides can seriously reduce the service life.

The flash point of the silicone fluid may be changed by heat-stressing. It is therefore particularly important in open systems to check the flash point at least once a year and more often if operating conditions demand.

## Packaging and storage

### Storage

The 'Best use before end' date of each batch is shown on the product label. Storage beyond the date specified on the label does not necessarily mean that the product is no longer usable. In this case however, the properties required for the intended use must be checked for quality assurance reasons.

## Safety notes

Comprehensive instructions are given in the corresponding Material Safety Data Sheets. They are available on request from WACKER subsidiaries or may be printed via WACKER web site <http://www.wacker.com>.

## QR Code WACKER® APF 130 STAB



### For technical, quality or product safety questions, please contact:

**Wacker Chemie AG**, Hanns-Seidel-Platz 4, 81737 Munich, Germany  
[info@wacker.com](mailto:info@wacker.com), [www.wacker.com](http://www.wacker.com)

The data presented in this medium are in accordance with the present state of our knowledge but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this medium should be checked by preliminary trials because of conditions during processing over which we have no control, especially where other companies' raw materials are also being used. The information provided by us does not absolve the user from the obligation of investigating the possibility of infringement of third parties' rights and, if necessary, clarifying the position. Recommendations for use do not constitute a warranty, either express or implied, of the fitness or suitability of the product for a particular purpose.