

WACKER[®] CATALYST EM 470

Catalysts

WACKER[®] CATALYST EM 470 is an emulsion containing highly reactive Platinum catalyst. The product is designed as a part in release coating formulations for the production of release papers and films.

Properties

- high reactivity
- very good wetting properties
- excellent anchorage
- high shear stability

Specific features

- Catalyst
- Emulsions

Technical data

General Characteristics

Property	Condition	Value	Method
Solid content	-	40 %	-
Appearance	-	milky, white	-
Density	20 °C	approx. 1 g/cm ³	-

These figures are only intended as a guide and should not be used in preparing specifications.

All the information provided is in accordance with the present state of our knowledge. Nonetheless, we disclaim any warranty or liability whatsoever and reserve the right, at any time, to effect technical alterations. The information provided, as well as the product's fitness for an intended application, should be checked by the buyer in preliminary trials. Contractual terms and conditions always take precedence. This disclaimer of warranty and liability also applies particularly in foreign countries with respect to third parties' rights.

Applications

- Baking Paper
- Food & Baking
- Industrial Applications
- Label
- Medical / Hygiene
- Release Coatings

Application details

WACKER® CATALYST EM 470 is compounded with Silicone Emulsion Crosslinkers and Dehesive® Emulsions. It is used to produce release liners for a variety of applications for paper and film based liners.

Processing

Before use, stir thoroughly.

1. Prepare the water quantity in a clean container while stirring slowly.
2. Add the Dehesive® polymer or polymer/crosslinker emulsion directly to the tank and mix at moderate shear.
3. In a next step add the crosslinker emulsion and continue mixing moderately.
4. Add the WACKER® CATALYST EM 470 in the last step and mix at moderate shear to achieve a homogeneous bath.
5. Please take care of perfect homogenization while adding WACKER® CATALYST EM 470 . Avoid local concentration peaks and catalyst poisons.

Packaging and storage

Storage

Store in a dry and cool place. Silicone emulsions are not freeze/thaw stable!

The 'Best use before end' date of each batch is printed on the product label.

Storage beyond the date specified on the label does not necessarily mean that the product is no longer usable. In this case however, the properties required for the intended use must be checked for quality assurance reasons.

Safety notes

Siloxane EM Catalysts should never get into direct contact with concentrated Siloxane Crosslinker Emulsions since this may cause an uncontrolled emission of hydrogen. The formation of hydrogen might lead together with air to explosive mixtures. Comprehensive safety information is given in the corresponding Material Safety Data Sheet. Comprehensive compliance information is given in the the corresponding Product Compliance Sheet. The sheets are available on request from WACKER subsidiaries or after registration on <http://www.wacker.com>.

QR Code WACKER® CATALYST EM 470



For technical, quality or product safety questions, please contact:

Wacker Chemie AG, Hanns-Seidel-Platz 4, 81737 Munich, Germany
info@wacker.com, www.wacker.com

The data presented in this medium are in accordance with the present state of our knowledge but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this medium should be checked by preliminary trials because of conditions during processing over which we have no control, especially where other companies' raw materials are also being used. The information provided by us does not absolve the user from the obligation of investigating the possibility of infringement of third parties' rights and, if necessary, clarifying the position. Recommendations for use do not constitute a warranty, either express or implied, of the fitness or suitability of the product for a particular purpose.