

WACKER

CREATING TOMORROW'S SOLUTIONS

ELASTOSIL®

PRODUCT OVERVIEW

INDUSTRIAL COATING OR SEALING APPLICATIONS

Flowable RTV silicone grades (self-adhesive)

Main characteristics	Brand	Product	Product type / curing system	Shrink-free curing	By-product of curing	Additional features	Food compliance	Viscosity [mPa·s]	Potlife or skin forming time	Hardness [Shore A]	Tensile strength [MPa]	Elongation at break [%]	Tear strength [N/mm]	Density, cured [g/cm ³]	Recommended max. service temperature [°C]	Aspect / color
Self-adhesive after curing at room temperature																
General purpose	ELASTOSIL®	A 07	RTV-1 / condensation cure		Amine	Solvent based		8,000	3 min	20	1.5	300	4.0	1.02	200	Translucent
	ELASTOSIL®	E 41	RTV-1 / condensation cure		Acetic acid	Solvent based		65,000	15 min	40	6.0	350	11.5	1.12	180	Translucent
	ELASTOSIL®	E 50 N	RTV-1 / condensation cure		Acetic acid	Titanium catalyzed	X	50,000	10 min	35	1.5	150	5.0	1.07	180	Transparent
	ELASTOSIL®	E 303	RTV-1 / condensation cure		Acetic acid	Solvent based		500	5 min	30	5.0	400		0.90	180	Translucent
	ELASTOSIL®	N 10	RTV-1 / condensation cure		Oxime			8,000	25 min	25	1.5	200	2.0	1.03	180	Transparent
	ELASTOSIL®	N 2010	RTV-1 / condensation cure		Alcohol			15,000	20 min	25	1.0	200		1.01	180	Translucent
	ELASTOSIL®	N 2034	RTV-1 / condensation cure		Alcohol	Flame retardant		25,000	20 min	35	2.0	200		1.16	180	Black
	ELASTOSIL®	RT 745	RTV-2 / platinum cure (A/B 1:1)	X				1,000	4 h	15	1.0	150		0.97	160	Brownish
Heat resistance	ELASTOSIL®	A 234	RTV-1 / condensation cure		Amine			35,000	15 min	36	2.5	200	3.7	1.19	230	White
	ELASTOSIL®	A 316	RTV-1 / condensation cure		Amine	Solvent based		500	5 min	15	0.8	200		1.02	180	Translucent
	ELASTOSIL®	A 59	RTV-1 / condensation cure		Amine	Oil resistant		60,000	45 min	20	1.2	300	3.0	1.43	210	Gray
	ELASTOSIL®	E 10	RTV-1 / condensation cure		Acetic acid			8,000	10 min	25	2.5	300	7.3	1.10	250	Red
	ELASTOSIL®	E 60 N	RTV-1 / condensation cure		Acetic acid	Titanium catalyzed	X	80,000	5 min	35	2.5	250		1.07	230	Black / gray / red
	ELASTOSIL®	N 288	RTV-1 / condensation cure		Oxime			65,000	50 min	35	3.5	300	5.1	1.09	230	Red
	ELASTOSIL®	N 291	RTV-1 / condensation cure		Oxime	Screen printable		45,000	6 h	40	2.5	200	5.5	1.21	200	Cream white
	ELASTOSIL®	N 294	RTV-1 / condensation cure		Oxime	Screen printable		25,000	6 h	33	2.2	200	4.5	1.21	200	Blue / red
ELASTOSIL®	RT 772	RTV-2 / condensation cure (Base + Catalyst 10:1)*		Alcohol			35,000	5 min / 10 min *	35	2.2	200		1.26	230	Black	
Self-adhesive after curing at elevated temperature																
Heat resistance	ELASTOSIL®	RT 705	1-component heat-curing / platinum cure	X				72,500	6 months	42	3.5	200	3.5	1.24	230	Black
	ELASTOSIL®	RT 706	1-component heat-curing / platinum cure	X				15,000	6 months	30	2.5	200		1.23	210	Red
	ELASTOSIL®	RT 707 W	1-component heat-curing / platinum cure	X				60,000	6 months	42	3.3	270		1.18	230	White
	ELASTOSIL®	RT 708	1-component heat-curing / platinum cure	X		UV fluorescent		75,000	6 months	42	3.5	300		1.36	230	Dark gray
High tear resistance	ELASTOSIL®	RT 720	RTV-2 / platinum cure (A/B 1:1)	X				35,000	6 h	40	6.0	300		1.10	180	Gray

* base component to be combined with WACKER® Catalyst T 77 or WACKER® Catalyst T 77 PLUS (please see the corresponding technical data sheet for details)

WACKER

Wacker Chemie AG
Hanns-Seidel-Platz 4
81737 München, Germany
Tel. +49 89 6279-1741
info@wacker.com

www.wacker.com

www.wacker.com/socialmedia



The data presented in this medium are in accordance with the present state of our knowledge but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this medium should be checked by preliminary trials because of conditions during processing over which we have no control, especially where other companies' raw materials are also being used. The information provided by us does not absolve the user from the obligation of investigating the possibility of infringement of third parties' rights and, if necessary, clarifying the position. Recommendations for use do not constitute a warranty, either express or implied, of the fitness or suitability of the product for a particular purpose.

7461C e/02.19 replaces 7461C e/08.17