

INFO SHEET | SILPURAN® | RELEASE LINERS FOR SILICONE SKIN ADHESIVE GELS

EASY RELEASE FOR SILPURAN® ADHESIVE GELS

PP and PE Substrate Release Liner Solutions for Skin Contact Applications

WACKER silicone adhesive gels have contributed to the steady improvement of professional wound care for over 20 years. They satisfy the highest medical standards by enabling secure fixation on skin without compromising gentle and atraumatic removal.

Recent developments in wound care have increased the demand for strong skin adhesives, as there is a trend toward longer wear time to reduce treatment costs as well as a rapidly growing market for wearable medical devices.

This opens up a whole range of new opportunities for coaters, processing companies and OEMs to develop a variety of new products for use in these applications.

To allow developers to concentrate on new products, WACKER is happy to advise you on release liner combinations that meet your application needs.

SILPURAN® High Adhesion Gels for Wearables


Over the recent past, we have added high adhesion strength silicone skin adhesives such as SILPURAN® 2114 and 2124. These products allow our customers to participate in the growing market of applications like wearables, which require longer wear time, mobility and stronger load-bearing properties. The soft but strong adhesive gels deliver the painless removal and repositioning properties for which our silicones are known so well.

Adhesive/Liner System Performance

Skin adhesive gels are typically used as part of a system requiring uncompromised adhesion to the backing layer combined with low adhesion to the release liner. Release liners are an essential part of the ultimate product as the applications require proven system performance as a whole.



Bandage with release liner



Release Liner Requirements

The basic function of release liners is to protect the adhesive layer of the medical device. Release liners for skin applications must meet certain key requirements:

- Adjustable smooth and stable release
- Conformability
- Regulatory compliance
- Sterilizability
- Suitability for die-cutting
- Printability

Easy-to-Use Combinations

There are several well-established release liner solutions for soft silicone adhesives with low to medium adhesion strength that meet all the above requirements. As higher adhesion silicone gels can be more challenging, we ran a test program to identify easy-to-use release liners. The graphs below show high-performing

combinations of SILPURAN® 2114 adhesive gel in combination with selected Loparex release liners. In all cases, the peel strength remains below 0.5 N/in and is stable over time, thus increasing the shelf life of the end product.



The release liner can easily be removed from the silicone adhesive coating.

Selecting Optimal Release Liners

When it comes to the right combination of adhesive and liner, a number of things need to be considered:

- Material compatibility can have a significant impact on performance
- The liner should release without removing adhesive upon peel
- Increase in peel force should be less than 2.5 x after 9 weeks at room temperature
- The peel force should not exceed 0.5 N/in

Benefits Along the Value Chain

It is our aim at WACKER to support our customers the best we can, so that they can bring successful products to market faster. The results of our test program on adhesive gel and release liner combinations can help developers avoid iterations and reduce risk by optimizing costs and performance.

Release Liner Performance on SILPURAN® 2114



Wacker Chemie AG, Hanns-Seidel-Platz 4, 81737 Munich, Germany, www.wacker.com/contact, www.wacker.com

Follow us on:

The data presented in this medium are in accordance with the present state of our knowledge but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this medium should be checked by preliminary trials because of conditions during processing over which we have no control, especially where other companies' raw materials are also being used. The information provided by us does not absolve the user from the obligation of investigating the possibility of infringement of third parties' rights and, if necessary, clarifying the position. Recommendations for use do not constitute a warranty, either express or implied, of the fitness or suitability of the product for a particular purpose.