

SILRES[®] REN 168



Silicone Resins

SILRES[®] REN 168 is a solid, silanol functional methylphenyl silicone resin recommended for the silicone modification of organic resins e.g. silicone polyester.

Properties

Used to improve the weather and heat resistance of paints.

Is FDA 21 CFR 175.300 and BfR XV compliant.

Used as chemically bound intermediates in organic polymers.

> 99% solid resin

Technical data

General Characteristics

Property	Condition	Value	Method
Color	-	colourless to yellowish	-
Hydroxyl content	-	3.5 - 7.5 %	-
Silicone content	-	> 98 %	-
Softening point	-	55 - 80 °C	-
Supply form	-	Flakes	-

These figures are only intended as a guide and should not be used in preparing specifications.

All the information provided is in accordance with the present state of our knowledge. Nonetheless, we disclaim any warranty or liability whatsoever and reserve the right, at any time, to effect technical alterations. The information provided, as well as the product's fitness for an intended application, should be checked by the buyer in preliminary trials. Contractual terms and conditions always take precedence. This disclaimer of warranty and liability also applies particularly in foreign countries with respect to third parties' rights.

Applications

- Battery
- Heat-Resistant Coatings
- Industrial Coatings
- Resin Modification for Coatings

Application details

SILRES® REN 168 is highly suitable for introducing a compatible silicone component into other binder systems to increase the weathering or heat resistance.

Guide formulations are available on request.

Application examples are:

- pots and pans
- coil coating
- appliance industry

Packaging and storage

Storage

The "Best use before end" date of each batch is shown on the product label.

Storage beyond the date specified on the label does not necessarily mean that the product is no longer usable. In this case however, the properties required for the intended use must be checked for quality assurance reasons.

Safety notes

Comprehensive instructions are given in the corresponding Material Safety Data Sheets. They are available on request from WACKER subsidiaries or may be printed via WACKER web site <http://www.wacker.com>.

QR Code SILRES® REN 168



For technical, quality or product safety questions, please contact:

Wacker Chemie AG, Gisela-Stein-Strasse 1, 81671 Munich, Germany
productinformation@wacker.com, www.wacker.com

The data presented in this medium are in accordance with the present state of our knowledge but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this medium should be checked by preliminary trials because of conditions during processing over which we have no control, especially where other companies' raw materials are also being used. The information provided by us does not absolve the user from the obligation of investigating the possibility of infringement of third parties' rights and, if necessary, clarifying the position. Recommendations for use do not constitute a warranty, either express or implied, of the fitness or suitability of the product for a particular purpose.