

ELASTOSIL® COLOR PASTE PT GREY RAL 7040



Silicone Rubber Additives

ELASTOSIL® COLOR PASTE PT GREY RAL 7040 is a ready-to-use compound comprising specific color pigments and a reactive silicone polymer which is commonly used in ELASTOSIL® high-consistency silicone rubber. This ensures a homogeneous covulcanization of the color paste without interference of the physical properties (e.g. hardness) and without migration as observed with silicone oil.

Properties

ELASTOSIL® COLOR PASTE PT GREY RAL 7040 is ready-to-use and can be easily incorporated on an open roll mill or kneader. ELASTOSIL® Color Pastes PT can be blended with each other to achieve a desired custom color tone. ELASTOSIL® COLOR PASTE PT GREY RAL 7040 is generally resistant to sunlight, UV and hot air. For further requirements the resistance should be checked in each individual case.

If the dosage recommendations are followed, the mechanical properties of the colored vulcanizates will not be impaired.

Specific features

- Product Type: Additive
- Regulation: BfR compliant
- Regulation: FDA compliant
- Specific Features: Additive
- Specific Features: BfR compliant
- Specific Features: FDA compliant
- Specific Features: Medical

Technical data

General Characteristics

Color Cure Conditions: 1 % in R plus 4001/40, 15 min / 165 °C in press

Color Measurement Conditions: CIE 1976 D65, 10°, d/8

Property	Condition	Value	Method
Appearance	-	grey, similar to RAL 7040	-
Density	-	1.70 g/cm ³	DIN EN ISO 1183-1 A
Coloristical properties	L* Value	68	DIN 5033
Coloristical properties	a* Value	-1	DIN 5033
Coloristical properties	b* Value	-1	DIN 5033

These figures are only intended as a guide and should not be used in preparing specifications.

All the information provided is in accordance with the present state of our knowledge. Nonetheless, we disclaim any warranty or liability whatsoever and reserve the right, at any time, to effect technical alterations. The information provided, as well as the product's fitness for an intended application, should be checked by the buyer in preliminary trials. Contractual terms and conditions always take precedence. This disclaimer of warranty and liability also applies particularly in foreign countries with respect to third parties' rights.

Application details

ELASTOSIL® COLOR PASTE PT GREY RAL 7040 has been developed particularly for coloring ELASTOSIL® R and ELASTOSIL® R plus high consistency silicone rubber.

ELASTOSIL® COLOR PASTE PT GREY RAL 7040 may be used for coloring silicone parts intended for sensitive applications and complying with the "Recommendation XV. Silicones" and "IX. Pigments for coloring plastics" of the BfR and FDA Regulation CFR 21 § 177.2600 "Rubber Articles Intended for Repeated Use" under observance of any given limitations on extractable and volatile substances. Please see the actual Product Compliance Sheet of this product and/or the separate Food Contact Statement for detailed information about food contact including information about any limitation in view of dosage and/or condition of use that may apply for this product.

A statement regarding biocompatibility according to USP<88> class VI and selected tests of ISO 10993 is available on request.

Processing

ELASTOSIL® COLOR PASTE PT GREY RAL 7040 is compatible with Curing Agents C1, and C6 for peroxide curing ELASTOSIL® R grades and is also fully compatible with addition curing ELASTOSIL® R plus grades. For crosslinker E, the compatibility has to be tested in the individual case.

Incorporation into ELASTOSIL® R and ELASTOSIL® R plus grades is best performed on an open roll mill. Preferably, the curing agent is incorporated at the same time. The color paste is homogeneously dispersed when the rubber stock has a uniform color. Customers may produce other colors by mixing the pigment pastes. Suggestions for formulations can be made on request.

A dosage of 1% ELASTOSIL® Color Paste PT is generally recommended to obtain opaque vulcanisates. For the manufacture of thin-walled parts and for rubber grades containing non-reinforcing fillers (e.g. quartz, diatomaceous earth) or colored additives (e.g. ELASTOSIL® AUX Stabilizer R, ELASTOSIL® AUX Batch SB 2) an increase of the dosage to 2 - 3% will be useful. The concentration should be kept at a minimum. In individual cases an excess of color paste may slow down the curing characteristics.

Packaging and storage

Packaging

This product is available in 20 kg cardboard packaging and 1kg tin.

Storage

Please store the cardboard boxes in a dry and cool place. Already opened boxes should be closed again to avoid any contamination.

The 'Best use before end' date of each batch is shown on the product label.

Storage beyond the date specified on the label does not necessarily mean that the product is no longer usable.

In this case however, the properties required for the intended use must be checked for quality assurance reasons.

Safety notes

Comprehensive instructions are given in the corresponding Material Safety Data Sheets. They are available on request from WACKER subsidiaries or may be printed via WACKER web site <http://www.wacker.com>.

QR Code ELASTOSIL® COLOR PASTE PT GREY RAL 7040



For technical, quality or product safety questions, please contact:

Wacker Chemie AG, Hanns-Seidel-Platz 4, 81737 Munich, Germany
info@wacker.com, www.wacker.com

The data presented in this medium are in accordance with the present state of our knowledge but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this medium should be checked by preliminary trials because of conditions during processing over which we have no control, especially where other companies' raw materials are also being used. The information provided by us does not absolve the user from the obligation of investigating the possibility of infringement of third parties' rights and, if necessary, clarifying the position. Recommendations for use do not constitute a warranty, either express or implied, of the fitness or suitability of the product for a particular purpose.