

ELASTOSIL[®] R 781/80 OH



High Consistency Silicone Rubber (HCR/HTV)

ELASTOSIL[®] R 781/80 is a magnetite filled high consistency rubber for molding and extrusion applications. It can be processed directly or be blended with other ELASTOSIL[®] R or R plus grades.

Properties

This product can be used within a temperature range of - 55 °C to + 210 °C. The addition of heat stabilizers at service temperatures of more than 180 °C is recommended. Further information to improve the heat stability by use of specific ELASTOSIL[®] AUX Heat Stabilizers can be obtained from the Technical Information Sheet "ELASTOSIL[®] AUX Stabilizers H" or from the latest brochures.

- rubber base containing 70% magnetite
- crosslinkable using standard peroxides or the ELASTOSIL[®] 4K system
- can be processed directly or blended with all ELASTOSIL[®] and R plus grades

Specific features

- Food-contact
- Magnetizable

Technical data

Properties Cured

Cure conditions:

0.7 % ELASTOSIL® AUX Crosslinker C1 (Dicumylperoxide); 15 min / 165 °C in press, post-cured 4 h / 200 °C

Property	Condition	Value	Method
Appearance and color	-	black	-
Hardness Shore A	-	80	DIN ISO 48-4
Density	-	2.43 g/cm ³	DIN EN ISO 1183-1 A
Tensile strength	-	5.3 N/mm ²	ISO 37 type 1
Elongation at break	-	100 %	ISO 37 type 1
Tear strength	-	15 N/mm	ASTM D 624 B
Rebound resilience	-	55 %	ISO 4662

These figures are only intended as a guide and should not be used in preparing specifications.

Properties Cured

Cure conditions:

1.5 % ELASTOSIL® AUX Crosslinker E (50% paste of bis-(2,4-dichlorobenzoyl)-peroxide in silicone fluid), 10 min / 135 °C in press, post-cured 4 h / 200 °C

Property	Condition	Curing Agent E	Method
Appearance and color	-	black	-
Hardness Shore A	-	83	DIN ISO 48-4
Density	-	2.43 g/cm ³	DIN EN ISO 1183-1 A
Tensile strength	-	3.3 N/mm ²	ISO 37 type 1
Elongation at break	-	50 %	ISO 37 type 1
Tear strength	-	18.0 N/mm	ASTM D 624 B
Rebound resilience	-	50 %	ISO 4662

These figures are only intended as a guide and should not be used in preparing specifications.

All the information provided is in accordance with the present state of our knowledge. Nonetheless, we disclaim any warranty or liability whatsoever and reserve the right, at any time, to effect technical alterations. The information provided, as well as the product's fitness for an intended application, should be checked by the buyer in preliminary trials. Contractual terms and conditions always take precedence. This disclaimer of warranty and liability also applies particularly in foreign countries with respect to third parties' rights.

Applications

- Dairy & Food Applications
- Molded Parts
- Profiles & Tubings

Application details

Postcured parts can be used for food contact applications and are suitable for use under the Recommendation "XV. Silicones" of the BfR and FDA § 177.2600 under observance of any given limitations on extractable and volatile substances.

Processing

ELASTOSIL® R 781/80 may be vulcanized using ELASTOSIL® AUX CURING AGENT C1, C6. Due to the high filler content it is recommended to reduce the content of peroxides to 50 % of the normally applied amounts when ELASTOSIL® R 781/80 is processed directly.

As an alternative crosslinking system the ELASTOSIL® 4K system may be applied. For further information on this topic please contact your responsible sales or technical manager.

The raw rubber requires the addition of peroxides for vulcanization at elevated temperatures. A homogeneous incorporation is a must to maintain best processing behavior. Pot life is depending on the used peroxide and storage condition. Please consider the technical data sheet of the corresponding curing agent.

For detailed information refer to our latest brochure "SOLID AND LIQUID SILICONE RUBBER - MATERIAL AND PROCESSING GUIDELINES".

Packaging and storage

Packaging

This product is available in 20 kg and 540 kg cardboard packaging.

Special delivery forms are possible but depend on several technical and commercial aspects. Please contact your local sales manager in such cases.

Storage

Please store the cardboard boxes in a dry and cool place. Already opened boxes should be closed again to avoid any contamination. The 'Best use before end' date of each batch is shown on the product label. Storage beyond the date specified on the label does not necessarily mean that the product is no longer usable. In this case however, the properties required for the intended use must be checked for quality assurance reasons.

Safety notes

Comprehensive instructions are given in the corresponding Material Safety Data Sheets. They are available on request from WACKER subsidiaries or may be printed via WACKER web site <http://www.wacker.com>.

QR Code ELASTOSIL® R 781/80 OH



For technical, quality or product safety questions, please contact:

Wacker Chemie AG, Hanns-Seidel-Platz 4, 81737 Munich, Germany
productinformation@wacker.com, www.wacker.com

The data presented in this medium are in accordance with the present state of our knowledge but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this medium should be checked by preliminary trials because of conditions during processing over which we have no control, especially where other companies' raw materials are also being used. The information provided by us does not absolve the user from the obligation of investigating the possibility of infringement of third parties' rights and, if necessary, clarifying the position. Recommendations for use do not constitute a warranty, either express or implied, of the fitness or suitability of the product for a particular purpose.