

SILFOAM[®] SRE



Silicone Antifoam Emulsions

SILFOAM[®] SRE, which contains 20% active ingredient and 33% solids, is a versatile antifoam that is comparatively rich in emulsifier but is nonetheless easily metered because it has a relatively low viscosity.

Since SILFOAM[®] SRE also possesses high resistance to alkalis and acids, it may further be used in a wide range of applications in which pH is critical.

Properties

Specific features

- Defoaming
- Dilutable with water
- Emulsions

Technical data

General Characteristics

Property	Condition	Value	Method
Appearance	-	white	-
Active ingredients content	-	approx. 20 %	-
Density	20 °C	approx. 1 g/cm ³	DIN 12791
Ionogenicity	-	nonionic	-
Solid content	-	approx. 33 %	Microwave oven
Viscosity, dynamic	25 °C Brookfield, spindle 1 / 50 rpm	approx. 20 - 2500 mPa·s	Brookfield
pH	-	approx. 5 - 8	Indicator strips

These figures are only intended as a guide and should not be used in preparing specifications.

All the information provided is in accordance with the present state of our knowledge. Nonetheless, we disclaim any warranty or liability whatsoever and reserve the right, at any time, to effect technical alterations. The information provided, as well as the product's fitness for an intended application, should be checked by the buyer in preliminary trials. Contractual terms and conditions always take precedence. This disclaimer of warranty and liability also applies particularly in foreign countries with respect to third parties' rights.

Applications

- Antifoams for Textile Finishing
- Agricultural Solutions
- Household & Cleaning Solutions

Application details

SILFOAM[®] SRE has proved ideal for tackling foam in textile auxiliaries and processes, for incorporation into cooling lubricants based on mineral oils, for separation of monomers from dispersions and conversion of dispersion into derivatives. SILFOAM[®] SRE is a useful auxiliary for combating foam generated in surfactant containing formulations employed in the most diverse areas, such as the agrochemicals (plant protection agents), cleaners and petrochemicals industries. SILFOAM[®] SRE is also an efficient defoamer for treating waste water.

Processing

SILFOAM[®] SRE is a low-viscosity emulsion, it can be metered readily, with stable dispersions easily attainable in high-viscosity formulations. In low viscosity products, preliminary compatibility and stability tests should be performed on the system to be defoamed. The amount to add to liquid formulations depends on the desired degree of foam control, but usually lies between 0.1 and 2 %.

If SILFOAM[®] SRE is to be added during a process, we recommend prediluting it with cold water in a ratio of 1:1 to 1:10. These diluted emulsions have a lower storage stability and should be processed as close in time as possible. If feed pumps are used, they should be of the low shear force type.

Packaging and storage

Storage

The 'Best use before end' date of each batch is shown on the product label.

Storage beyond the date specified on the label does not necessarily mean that the product is no longer usable. In this case however, the properties required for the intended use must be checked for quality assurance reasons.

Safety notes

Comprehensive instructions are given in the corresponding Material Safety Data Sheets. They are available on request from WACKER subsidiaries or may be printed via WACKER web site <http://www.wacker.com>.

QR Code SILFOAM® SRE



For technical, quality or product safety questions, please contact:

Wacker Chemie AG, Hanns-Seidel-Platz 4, 81737 Munich, Germany
productinformation@wacker.com, www.wacker.com

The data presented in this medium are in accordance with the present state of our knowledge but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this medium should be checked by preliminary trials because of conditions during processing over which we have no control, especially where other companies' raw materials are also being used. The information provided by us does not absolve the user from the obligation of investigating the possibility of infringement of third parties' rights and, if necessary, clarifying the position. Recommendations for use do not constitute a warranty, either express or implied, of the fitness or suitability of the product for a particular purpose.