

SILRES[®] BS 94



Functional Silicone Fluids

SILRES[®] BS 94 is a highly effective, anhydrous silicone based on polymethylhydrogensiloxane.

Technical data

General Characteristics

Property	Condition	Value	Method
Refractive index	-	approx. 1.396	-
Appearance	-	colorless liquid	-
Active substance	-	100 wt. %	-
Density	25 °C 1013 hPa	1.0 g/cm ³	DIN 51757
Flash point	-	115 °C	ISO 2719
Flash point	-	> 110 °C	ISO 3679
Ignition temperature (liquids)	-	285 °C	DIN 51794
Odor	-	not characteristic	-
Viscosity, kinematic	25 °C	20 - 25 mm ² /s	DIN 51562
Volatiles	-	max. 1.5 wt. %	-

These figures are only intended as a guide and should not be used in preparing specifications.

All the information provided is in accordance with the present state of our knowledge. Nonetheless, we disclaim any warranty or liability whatsoever and reserve the right, at any time, to effect technical alterations. The information provided, as well as the product's fitness for an intended application, should be checked by the buyer in preliminary trials. Contractual terms and conditions always take precedence. This disclaimer of warranty and liability also applies particularly in foreign countries with respect to third parties' rights.

Applications

- Gypsum Wallboards and Gypsum Fiberboards

Application details

Water-repellent treatment of plaster elements and plasterboard / wallboard.

SILRES® BS 94 is added to the mixing / gauging water of the plaster. The addition of just 0.2-0.4% SILRES® BS 94, expressed in terms of the plaster, effects a marked reduction in water absorbency as required by DIN EN 520.

The efficiency of SILRES® BS 94 depends on the kind of plaster, on the water / gypsum ratio and on additives such as starch / cellulose or surfactants. This is why no general recommendations on the dosage of SILRES® BS 94 can be given. Preliminary tests are always necessary for establishing the required amount.

Alkaline components of the plaster may lead to diminution of the bulk density and the water repellency of the plaster elements.

SILRES® BS 94 is not recommended for surface treatment of plaster elements.

Suggested formulation for laboratory tests: 1,25g of SILRES® BS 94 is mixed into 400g of deionized water with a turbine mixer (at least 1,000rpm) for 30 seconds. 500g of plaster of paris is added to this mixture. The mixture stirred with a paddle mixer for one minute and then poured into PVC rings (diameter: 8cm, height: 2cm). After setting, the samples are removed from the PVC rings and dried for 24 hours at 40°C in an exhaust hot-air cabinet with open flap. Subsequently the samples are dried for six days of room temperature during that time they will reach their constant weight.

To determine water absorbency, the samples are placed horizontally into deionized water so that they are covered by 5cm of water (DIN EN 520). After 2 hours they are taken out, the remaining drops on the surface are removed and the samples are weighed. The mean water absorbency of at least 3 samples is calculated terms of the dry weight of the plaster samples before immersion in water. Untreated samples produced by the same method have a water absorbency of about 50%.

Packaging and storage

Storage

SILRES® BS 94 must be stored in the tightly closed original container under exclusion of moisture.

The 'Best use before end' date of each batch is shown on the product label. Storage beyond the date specified on the label does not necessarily mean that the product is no longer usable. In this case however, the properties required for the intended use must be checked for quality assurance reasons.

Safety notes

Comprehensive instructions are given in the corresponding Material Safety Data Sheets. They are available on request from WACKER subsidiaries or may be printed via WACKER web site <http://www.wacker.com>.

QR Code SILRES® BS 94



For technical, quality or product safety questions, please contact:

Wacker Chemie AG, Hanns-Seidel-Platz 4, 81737 Munich, Germany
info@wacker.com, www.wacker.com

The data presented in this medium are in accordance with the present state of our knowledge but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this medium should be checked by preliminary trials because of conditions during processing over which we have no control, especially where other companies' raw materials are also being used. The information provided by us does not absolve the user from the obligation of investigating the possibility of infringement of third parties' rights and, if necessary, clarifying the position. Recommendations for use do not constitute a warranty, either express or implied, of the fitness or suitability of the product for a particular purpose.