

VINNOL[®] E 18/38



Vinyl chloride Co- and Terpolymers

VINNOL[®] E 18/38 is a copolymer of approx. 82 wt.% vinyl chloride (VC) and approx. 18 wt.% of vinyl acetate (VAc).

Its main use is as a binder for printing inks and surface coating compounds.

Properties

VINNOL[®] E 18/38 is a thermoplastic, physically drying binder that forms a film when the solvent contained in the formulation has evaporated.

Like all VC copolymers, VINNOL[®] E 18/38 is extremely tough, showing permanent flexibility, abrasion resistance, little tendency to swell in the presence of water and low gas permeability. It is also highly resistant to oil, grease, dilute aqueous acids, alkalis and saline solutions, as well as to aliphatic hydrocarbons, such as white spirit, and alcohols.

Technical data

Specification

Property	Condition	Value	Method
K-value	-	37 - 39	DIN EN ISO 1628-2
Viscosity, dynamic (20% in MEK) ⁽¹⁾	20 °C	11 - 19 mPa·s	DIN 53015 (20°C)
Chlorine content	-	45.4 - 46.6 wt. %	specific method
Volatiles	-	< 0.5 wt. %	specific method

¹after dissolving at 50 °C

General Characteristics

Property	Condition	Value	Method
Efflux time (20% in MEK)	-	approx. 21 s	DIN EN ISO 2431 (4 mm)
Supply form	-	white granulate with some powder	Visual
Bulk density	-	approx. 550 kg/m ³	DIN EN ISO 60
Density	-	1.36 g/cm ³	DIN 66137-2
Glass transition temperature	-	approx. 70 °C	DSC (DIN 53765 / ISO 11357-5)
Molecular weight (Mw)	-	33000 - 43000 g/mol	SEC, PS-Standard
Particle size	-	< 2.5 mm	specific method

These figures are only intended as a guide and should not be used in preparing specifications.

All the information provided is in accordance with the present state of our knowledge. Nonetheless, we disclaim any warranty or liability whatsoever and reserve the right, at any time, to effect technical alterations. The information provided, as well as the product's fitness for an intended application, should be checked by the buyer in preliminary trials. Contractual terms and conditions always take precedence. This disclaimer of warranty and liability also applies particularly in foreign countries with respect to third parties' rights.

Applications

- Gravure Printing
- Industrial Wood Coatings
- Inkjet
- Marine & Protective Coatings
- Pad Printing
- Plastic Coatings
- Screen Printing

- Strippable Coatings
- Transfer Printing

Application details

Typical applications for VINNOL® E 18/38:

- Printing inks, especially inkjet inks
- Pigment preparations
- Paper and film coatings
- Protective and masonry paints

Processing

VINNOL® E 18/38 is typically used in dissolved form.

Ketones and esters are the solvents most commonly used for VINNOL® E 18/38, ketones being more efficient than esters. Various glycol esters (e.g. butyl glycol acetate) and glycol ethers can also be used as solvents, their suitability needs to be checked on a case by case basis. Alcohols and aliphatic hydrocarbons do not dissolve VINNOL® E 18/38. Aromatic hydrocarbons may be combined to a limited extent with true solvents.

VINNOL® E 18/38 can be plasticized with monomeric and polymeric plasticizers, such as phthalates, adipates, sebacates, citrates, phosphates, epoxides and chlorinated paraffins.

VINNOL® E 18/38 is fully compatible with all other VINNOL® surface coating resins. It also combines well with many acrylic polymers and ketone resins, as well as with some epoxides. Alkyd, nitrocellulose, polyvinyl acetate and polyvinyl butyral resins are typically incompatible with VINNOL® E 18/38. We recommend to always check the compatibility of VINNOL® E 18/38 with potential blending partners.

VINNOL® E 18/38 shows high compatibility with pigments routinely used in the coatings industry. Care must be taken when using pigments containing zinc or cadmium because these catalyze the decomposition of VC copolymers at elevated temperatures. The same applies to iron-oxide pigments.

Despite good inherent stability, it is necessary for some applications to stabilize coatings based on VINNOL® E 18/38 against heat and/or UV light. Epoxy compounds often suffice to stabilize these coatings against low thermal impact. Where higher temperatures are involved, it is advisable to use calcium/zinc or organotin stabilizers. Outdoor applications require the additional use of UV stabilizers along with thermal stabilizers optimized for these conditions.

To avoid risk of discoloration, contact with iron should be avoided both during preparation of the solution and during subsequent storage of the product. VINNOL®-based surface-coating resins should be stored in coated containers.

Additional Information

The product can be used for applications with food contact in compliance with FDA 21 CFR §175.105 and §175.300. Comprehensive information regarding evaluation with respect to other food contact regulations may be requested from our account managers and Wacker subsidiaries.

If the product is used in applications other than those mentioned, the choice, processing and use of the product is the sole responsibility of the purchaser. All legal and other regulations must be complied with.

Packaging and storage

Packaging

VINNOL® E 18/38 is packed in 25-kg, coated three-ply paper bags containing a polyethylene liner.

Storage

Store VINNOL® E 18/38 under dry conditions and at room temperature (below 25°C). If proper conditions are maintained, the product has a shelf life of at least 12 months from the delivery date if stored in the original, unopened containers. Beyond its recommended shelf life, the product is not necessarily unusable, but the user should perform quality control regarding the properties relevant to the application.

Safety notes

Comprehensive instructions are given in the appropriate Material Safety Data Sheets. These are available on request from WACKER sales offices or may be downloaded from the WACKER web site:
www.wacker.com/vinnol

QR Code VINNOL® E 18/38



For technical, quality or product safety questions, please contact:

Wacker Chemie AG, Hanns-Seidel-Platz 4, 81737 Munich, Germany
productinformation@wacker.com, www.wacker.com

The data presented in this medium are in accordance with the present state of our knowledge but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this medium should be checked by preliminary trials because of conditions during processing over which we have no control, especially where other companies' raw materials are also being used. The information provided by us does not absolve the user from the obligation of investigating the possibility of infringement of third parties' rights and, if necessary, clarifying the position. Recommendations for use do not constitute a warranty, either express or implied, of the fitness or suitability of the product for a particular purpose.