

# WACKER® CROSSLINKER V 72

# **Curing Agents**

WACKER® CROSSLINKER V 72 is an emulsified hydrogenpolysiloxane containing reactive Si-H groups. It is designed as part for of a emulsion release coating system on a variety of substrates.

# **Properties**

- superior curing allows for low platinum formulation
- easy mixing and metering
- good release stability
- good bath life
- excellent wetting properties

#### Specific features

- Crosslinker
- Emulsions

#### Technical data

#### **General Characteristics**

Property	Condition	Value	Method
Appearance	-	milky, white	visual check
Content	-	38.0 %	-
Density	20 °C	approx. 1 g/cm³	DIN 51757

These figures are only intended as a guide and should not be used in preparing specifications.

All the information provided is in accordance with the present state of our knowledge. Nonetheless, we disclaim any warranty or liability whatsoever and reserve the right, at any time, to effect technical alterations. The information provided, as well as the product's fitness for an intended application, should be checked by the buyer in preliminary trials. Contractual terms and conditions always take precedence. This disclaimer of warranty and liability also applies particularly in foreign countries with respect to third parties' rights.

### **Applications**

- Baking Paper
- Label
- · Medical / Hygiene
- · Release Coatings

# Application details

WACKER® CROSSLINKER V 72 is compounded with Silicone Catalyst Emulsions and DEHESIVE® Emulsions. It used to produce release liners especially on filmic substrates.

# **Processing**

Before use, stir thoroughly.

- 1. Prepare the water quantity in a clean container while stirring slowly.
- 2. Add the Dehesive® polymer Emulsion directly to the tank and mix at moderate shear.
- 3. In a next step add the crosslinker emulsion and continue mixing moderatedly.
- 4. Add the Catalyst–EM in the last step and mix at moderate shear to achieve a homogeneous bath. Please take care of perfect homogenization while adding the Catalyst-EM.

Avoid local concentration peaks and catalyst poisons.

# Packaging and storage

#### Storage

Store in a dry and cool place. Silicone emulsions are not freeze/thaw stable!

The 'Best use before end' date of each batch is printed on the product label.

Storage beyond the date specified on the label does not necessarily mean that the product is no longer usable. In this case however, the properties required for the intended use must be checked for quality assurance reasons.

# Safety notes

Siloxane Crosslinker Emulsions should never get into direct contact with concentrated Siloxane Catalyst Emuslions or Alkaline Systems, since this may cause a spontaneous, uncontrolled emission of hydrogen. The formation of hydrogen might lead together with air to the explosive mixtures.

Comprehensive safety information is given in the corresponding Material Safety Data Sheet.

Comprehensive compliance information is given in the the corresponding Product Compliance Sheet.

The sheets are available on request from WACKER subsidiaries or after registration on http://www.wacker.com.

#### QR Code WACKER® CROSSLINKER V 72



#### For technical, quality or product safety questions, please contact:

Wacker Chemie AG, Hanns-Seidel-Platz 4, 81737 Munich, Germany productinformation@wacker.com, www.wacker.com

The data presented in this medium are in accordance with the present state of our knowledge but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this medium should be checked by preliminary trials because of conditions during processing over which we have no control, especially where other companies' raw materials are also being used. The information provided by us does not absolve the user from the obligation of investigating the possibility of infringement of third parties' rights and, if necessary, clarifying the position. Recommendations for use do not constitute a warranty, either express or implied, of the fitness or suitability of the product for a particular purpose.