

# WACKER® W 23

## Silicone Waxes

WACKER® W 23 is a white, waxy, alkyl modified polysiloxane that is resistant to hydrolysis and exhibits a very high affinity to various substrates.

## Technical data

### General Characteristics

| Property           | Condition | Value                  | Method        |
|--------------------|-----------|------------------------|---------------|
| Appearance         | -         | white, wax-like        | -             |
| Density            | 50 °C     | 0.85 g/cm <sup>3</sup> | not specified |
| Melting point      | -         | approx. 42 °C          | -             |
| Viscosity, dynamic | 50 °C     | 300 mPa·s              | Brookfield    |

These figures are only intended as a guide and should not be used in preparing specifications.

All the information provided is in accordance with the present state of our knowledge. Nonetheless, we disclaim any warranty or liability whatsoever and reserve the right, at any time, to effect technical alterations. The information provided, as well as the product's fitness for an intended application, should be checked by the buyer in preliminary trials. Contractual terms and conditions always take precedence. This disclaimer of warranty and liability also applies particularly in foreign countries with respect to third parties' rights.

## Applications

- Antifriction Agents & Lubricants
- Car Care
- Metal Care

- Paint polishes & paint conditioners
- Plastic-Care Products
- Polyurethane Processing
- Surface Care
- Textile and Leather Impregnation

## Application details

WACKER® W 23 is mainly used in the polishes sector. Due to the high substantivity, it is recommended for car polishes and paint conditioners, since it renders the treated paint surface extremely resistant to detergents and weathering for long periods of time.

## Packaging and storage

### Storage

The 'Best use before end' date of each batch is shown on the product label. Storage beyond the date specified on the label does not necessarily mean that the product is no longer usable. In this case however, the properties required for the intended use must be checked for quality assurance reasons.

## Safety notes

Comprehensive instructions are given in the corresponding Material Safety Data Sheets. They are available on request from WACKER subsidiaries or may be printed via WACKER web site <http://www.wacker.com>.

## QR Code WACKER® W 23



### For technical, quality or product safety questions, please contact:

**Wacker Chemie AG**, Gisela-Stein-Strasse 1, 81671 Munich, Germany  
[productinformation@wacker.com](mailto:productinformation@wacker.com), [www.wacker.com](http://www.wacker.com)

The data presented in this medium are in accordance with the present state of our knowledge but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this medium should be checked by preliminary trials because of conditions during processing over which we have no control, especially where other companies' raw materials are also being used. The information provided by us does not absolve the user from the obligation of investigating the possibility of infringement of third parties' rights and, if necessary, clarifying the position. Recommendations for use do not constitute a warranty, either express or implied, of the fitness or suitability of the product for a particular purpose.