

SILFOAM[®] SC 369



Silicone Antifoam Compound

SILFOAM[®] SC 369 is a medium viscosity antifoam agent that has an active ingredient content of 100 % and is based on an organically modified silicone fluid. In comparison to antifoam agents which are based on pure silicone fluids (PDMS), SILFOAM[®] SC 369 in general exhibits better compatibility with organic systems.

Properties

SILFOAM[®] SC 369 is recommended:

- for enhancing the effect of organic defoamers
- in applications where the use of silicones can cause problems, e. g., in the textile, paint and lacquer sectors and in cooling lubricants

Technical data

General Characteristics

Property	Condition	Value	Method
Appearance	-	colorless, opaque	-
Density	20 °C	approx. 1.065 g/cm ³	DIN 51757
Flash point	-	approx. 95 °C	ISO 2719
Ignition temperature	-	250 °C	DIN 51794
Refractive index	25 °C	approx. 1.424	DIN 51423
Viscosity, dynamic	25 °C	500 - 5000 mPa·s	-

These figures are only intended as a guide and should not be used in preparing specifications.

All the information provided is in accordance with the present state of our knowledge. Nonetheless, we disclaim any warranty or liability whatsoever and reserve the right, at any time, to effect technical alterations. The information provided, as well as the product's fitness for an intended application, should be checked by the buyer in preliminary trials. Contractual terms and conditions always take precedence. This disclaimer of warranty and liability also applies particularly in foreign countries with respect to third parties' rights.

Applications

- Antifoams

Application details

SILFOAM® SC 369 may be added as it is at high shear rates or in the form of a dispersion.

The degree of dilution should be as low as possible.

Suitable dispersing agents include ethanol, 2-propanol, acetone and 2-ethyl hexanol.

The exact dosage has to be determined in preliminary tests.

We recommend starting with amounts between 0.02 and 0.5 %.

After extended storage or if visible separation occurs, we recommend briefly stirring the product.

As a guideline, we suggest a stirring time of 10–30 minutes at a speed of 200 rpm.

Packaging and storage

Storage

The 'Best use before end' date of each batch is shown on the product label.

Storage beyond the date specified on the label does not necessarily mean that the product is no longer usable. In this case however, the properties required for the intended use must be checked for quality assurance reasons.

Safety notes

Comprehensive instructions are given in the corresponding Material Safety Data Sheets. They are available on request from WACKER subsidiaries or may be printed via WACKER web site <http://www.wacker.com>.

QR Code SILFOAM® SC 369



For technical, quality or product safety questions, please contact:

Wacker Chemie AG, Gisela-Stein-Strasse 1, 81671 Munich, Germany
productinformation@wacker.com, www.wacker.com

The data presented in this medium are in accordance with the present state of our knowledge but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this medium should be checked by preliminary trials because of conditions during processing over which we have no control, especially where other companies' raw materials are also being used. The information provided by us does not absolve the user from the obligation of investigating the possibility of infringement of third parties' rights and, if necessary, clarifying the position. Recommendations for use do not constitute a warranty, either express or implied, of the fitness or suitability of the product for a particular purpose.